

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
1-CHLORO-1-NITRO ETHANE	23	4	4	0	4	4	0	4	0	0	1	4	1
1-HEXENE	23	0	0	0	0	0	0	0	0	0	1	0	1
1-NITROPROPANE	23	3	4	4	4	4	0	4	0	0	1	3	0
2-CHLORO-P-TOLUIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
2-ETHYL HEXANOL (ISOOCTANOL)	23	0	0	0	0	0	0	0	0	0	1	0	1
51-F-23	23	4	1	1	2	3	0	1	1	1	1	2	1
ABIETIC ACID	23	1	3	3	4	2	0	3	1	1	1	4	1
ACETALDEHYDE	23	1	4	3	4	2	0	4	0	2	1	4	1
ACETAMIDE	23	1	1	1	4	2	1	2	0	0	1	4	1
ACETANILIDE	23	1	3	3	4	2	0	3	0	0	1	0	1
ACETIC ACID 10 %	50	1	4	4	4	1	0	1	4	3	1	3	0
ACETIC ACID 30%	23	1	4	0	4	1	0	2	2	2	1	4	1
ACETIC ACID 50 %	50	1	4	4	4	3	0	4	4	4	1	4	0
ACETIC ACID AMIDE	23	1	1	1	4	2	2	3	1	1	1	3	1
ACETIC ACID ETHYL ESTER	23	2	4	4	4	2	4	4	3	3	1	4	1
ACETIC ACID, GLACIAL	23	1	3	2	4	3	0	3	4	4	1	4	1
ACETIC ALDEHYDE	23	0	0	0	0	0	0	0	0	0	0	0	0
ACETIC ANHYDRIDE	23	2	4	4	4	3	2	4	4	3	1	4	1
ACETOACETIC ACID	23	1	3	3	4	2	3	4	2	2	1	4	1
ACETONE (DIMETHYLKETONE)	23	1	4	4	4	3	0	4	1	1	1	4	0
ACETONE CYANOHYDRIN	23	4	4	3	4	2	0	4	2	2	1	4	1
ACETONE/TOLUENE (50%/50%)	23	1	0	0	0	0	0	4	0	0	1	0	1
ACETONITRILE	23	1	3	3	4	2	1	4	0	0	1	4	1
ACETOPHENETIDIN	23	4	2	2	3	0	1	1	2	2	1	0	1
ACETOPHENONE	23	1	4	4	4	4	0	4	1	1	1	4	1
ACETOTOLUIDIDE	23	4	2	2	3	0	1	1	3	3	1	3	1
ACETYL ACETONE	23	1	4	4	4	4	4	4	2	2	1	4	1
ACETYL BROMIDE	23	1	4	4	4	4	2	1	2	2	1	4	1
ACETYL CHLORIDE	23	4	4	4	4	3	0	1	0	0	1	4	1
ACETYL NITRATE	23	0	0	0	0	0	0	0	0	0	0	0	0
ACETYLENE	23	1	1	1	4	3	1	1	1	1	1	2	0
ACETYLENE TETRABROMIDE	23	1	4	4	4	4	1	1	2	2	1	4	1
ACETYLENE TETRACHLORIDE	23	1	4	4	4	4	4	1	2	2	1	4	1
ACETYLSALICYLIC ACID	23	4	4	4	3	0	1	2	1	1	1	2	1
ACIDS, NON-ORGANIC	23	1	2	2	4	2	1	2	2	2	1	4	1
ACIDS, ORGANIC	23	1	2	2	0	3	1	3	0	0	1	0	1
ACONITIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
ACRIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
ACROLEIN	23	1	3	3	4	2	1	4	2	2	1	4	1
ACRYLIC ACID	23	4	4	4	4	4	2	4	2	3	1	4	1
ACRYLONITRILE	23	4	4	4	4	4	0	4	1	1	1	4	1
ACT™ 690C	23	0	0	0	0	0	0	0	0	0	1	0	1
ACT™ 935	23	0	0	0	0	0	0	0	0	0	1	0	1
ACT™ 970	23	0	0	0	0	0	0	0	0	0	1	0	1
ACT™ CMI	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
ACT™ K-101	23	0	0	0	0	0	0	0	0	0	1	0	1
ACT™ K-117	23	0	0	0	0	0	0	0	0	0	1	0	1
ACT™ NE-14	23	0	0	0	0	0	0	0	0	0	1	0	1
ADIPIC ACID	23	1	1	1	3	3	0	2	0	3	1	2	1
ADIPRENE L-167	23	1	2	1	4	0	0	2	1	1	1	4	1
AERO LUBRIPLATE	23	4	1	4	1	2	1	1	1	1	1	1	1
AERO SHELL 100	70	1	0	3	1	0	0	1	1	1	1	1	1
AERO SHELL 17 GREASE	23	4	1	1	1	2	1	1	1	1	1	1	1
AERO SHELL 750 GREASE	50	4	4	2	4	4	4	1	1	1	4	1	0
AERO SHELL 7A GREASE	50	4	2	2	1	3	2	1	1	1	4	1	0
AERO SHELL FLUID NO.4	80	4	1	1	1	4	0	1	1	1	1	1	0
AERO SHELL TURBINE OIL 760	23	0	0	0	0	0	0	1	1	1	1	1	1
AEROSAFE 2300	23	1	4	4	4	3	2	4	2	2	1	0	0
AEROSAFE 2300W	23	1	4	4	4	3	2	4	0	0	1	0	0
AEROZENE 50 (50% HYDRAZINE, 50%UDMH)	23	1	3	3	4	4	2	4	0	0	1	0	0
AIR < 93°C (200°F)	100	1	1	1	1	1	1	1	1	1	1	1	1
AIR 150 - 200°C (AIR 300 - 400°F)	200	4	4	4	4	1	1	1	4	4	1	4	4
AIR 200 - 260°C (AIR 400 - 500°F)	260	4	4	4	4	2	3	3	4	4	4	4	4
AIR 93 - 150°C (200 - 300°F)	150	2	3	3	3	1	1	1	0	0	1	0	0
AIR OIL-CONTAINING	23	4	1	1	1	1	1	1	1	1	1	1	0
ALCOHOL (DRINKING-ALCOHOL -40 VOL.%)	23	1	1	1	4	1	0	1	1	1	1	2	0
ALIPHATIC DICARBOXYLIC ACID	23	4	2	2	3	0	1	1	2	2	1	2	0
ALKANES (PARAFFIN HYDROCARBONS)	23	4	4	1	1	0	4	1	1	1	4	1	0
ALKANESULFONIC ACID	23	4	1	1	1	2	0	1	1	1	1	1	1
ALKAZENE (DIBROMOETHYLBENZENE)	23	4	4	4	4	4	2	2	0	0	1	4	0
ALKENES (OLEFIN HYDROCARBONS)	23	4	2	2	3	0	0	1	2	2	1	2	0
ALKYL ACETONE	23	1	3	3	4	2	0	4	2	2	1	4	0
ALKYL ALCOHOL	23	4	1	1	3	2	0	4	1	1	1	3	0
ALKYL AMINE	23	4	1	1	4	2	0	4	1	1	1	3	1
ALKYL BENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
ALKYL CHLORIDE	23	4	2	2	4	0	0	2	0	0	1	4	1
ALKYL SULFIDE	23	4	2	2	3	0	0	1	0	0	1	0	0
ALKYLARYL SULPHONATES	23	4	1	1	4	2	0	1	0	0	1	4	1
ALKYLARYL SULPHONICS	23	4	1	1	4	2	0	1	0	0	1	4	1
ALKYLNAPHTHALENE SULFONIC ACID	23	4	1	1	4	0	4	1	0	0	1	3	0
ALLYL ALCOHOL	23	2	2	2	4	2	0	4	0	2	1	4	2
ALLYL BROMIDE	23	1	0	0	4	0	0	0	0	0	2	0	0
ALLYLCHLORIDE	23	4	2	2	4	0	2	2	0	0	1	4	0
ALLYLIDENE DIACETATE	23	1	3	3	4	2	0	3	0	0	1	0	0
ALPHA PICOLINE (2-methylpyridine)	23	1	3	3	4	2	0	3	0	0	1	4	0
ALUM	23	1	1	1	0	0	0	1	0	0	1	0	0
ALUMINIUM FLUORSILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ALUMINUM ACETATE	23	1	2	2	4	4	1	4	0	0	1	4	0
ALUMINUM BROMIDE	23	1	1	1	3	1	1	1	1	1	1	2	1
ALUMINUM CHLORATE	23	1	3	3	4	1	0	3	1	1	1	3	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
ALUMINUM CHLORIDE	23	1	1	1	3	2	1	1	1	1	1	1	1
ALUMINUM ETHYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ALUMINUM FLUORIDE	23	1	1	1	3	2	0	1	1	1	1	2	1
ALUMINUM FORMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ALUMINUM HYDROXIDE	23	2	2	2	0	2	1	2	0	0	1	0	0
ALUMINUM LINOLEATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ALUMINUM NITRATE	23	0	0	0	4	0	0	1	0	0	1	0	1
ALUMINUM NITRATE (AQ)	23	1	1	1	4	3	0	1	0	0	1	3	1
ALUMINUM OXALATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ALUMINUM PHOSPHATE	23	1	1	1	4	1	0	1	1	3	1	2	1
ALUMINUM POTASSIUM SULFATE	23	0	0	0	0	0	0	1	0	0	1	0	1
ALUMINUM SALTS	23	1	1	1	3	0	0	1	0	0	1	0	0
ALUMINUM SODIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ALUMINUM SULFATE	23	1	1	1	4	0	0	1	0	0	1	4	0
ALUM-NH3-CR-K (AQ)	23	1	1	1	0	1	1	4	0	0	1	0	1
ALUMS	23	0	0	0	0	0	0	1	0	0	1	0	1
AMBREX 33	23	0	0	0	0	0	0	0	0	0	1	0	1
AMBREX 830	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINES	23	2	4	3	4	0	0	4	0	0	1	0	0
AMINO PHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINOANTHRAQUINONE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINOAZOBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINO BENZENE SULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINO BENZOIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINOETHYLETHANOLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINOPYRIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMINOSALICYLIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIA	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIA ANHYDROUS	23	1	2	2	4	3	0	4	0	0	1	4	1
AMMONIA GAS, COLD	23	1	1	1	3	1	2	4	0	0	1	1	1
AMMONIA GAS, HOT	23	2	4	4	4	1	0	4	0	0	1	4	0
AMMONIA SOLUTION 25%	23	1	3	3	4	1	0	3	1	3	1	2	0
AMMONIA, ANHYDROUS	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM ACETATE	23	1	1	0	4	0	0	1	0	0	1	0	1
AMMONIUM ARSENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM BENZOATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM BICARBONATE	23	1	1	0	0	0	0	4	0	0	1	0	1
AMMONIUM BIFLUORIDE	23	2	2	0	0	0	0	2	0	0	1	0	1
AMMONIUM BISULFITE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM CARBAMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM CARBONATE	23	1	4	4	4	3	1	2	0	3	1	4	1
AMMONIUM CHLORIDE	23	1	1	1	3	3	0	1	1	3	1	1	1
AMMONIUM CITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM COPPERSULFATE	23	1	0	0	3	0	0	0	0	0	1	0	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
AMMONIUM DICHROMATE	23	1	0	1	0	0	0	3	0	0	1	0	1
AMMONIUM DIPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM FLUORIDE	23	1	1	0	0	0	0	1	0	0	1	0	1
AMMONIUM FLUOSILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM FORMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM HYDROGEN FLUORIDE	23	1	0	0	0	0	0	2	0	0	1	0	1
AMMONIUM HYDROXIDE	23	1	2	2	4	0	0	2	0	0	1	4	0
AMMONIUM HYDROXIDE (CONC.)	23	1	4	4	4	1	0	2	0	0	1	4	1
AMMONIUM HYDROXIDE (DIL.)	23	1	1	1	4	1	0	1	1	3	1	2	1
AMMONIUM IODIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM LACTATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM METAPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM MOLYBDATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM NITRATE	23	1	1	1	4	0	1	2	0	0	1	4	1
AMMONIUM NITRITE	23	1	1	1	4	2	0	3	0	0	1	0	1
AMMONIUM OXALATE	23	1	0	0	0	0	0	0	0	0	0	0	1
AMMONIUM PERCHLORATE	23	1	0	0	0	0	0	0	0	0	0	0	1
AMMONIUM PERCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM PERSULFATE	23	1	4	4	4	4	0	3	1	3	1	4	1
AMMONIUM PHOSPHATE	23	1	1	1	4	1	0	4	0	0	1	0	1
AMMONIUM PHOSPHATE (DIBASIC)	23	0	0	0	0	0	0	1	0	0	1	0	1
AMMONIUM PHOSPHATE (DI-BASIC)	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM PHOSPHATE (MONOBASIC)	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM PHOSPHATE (MONO-BASIC)	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM PHOSPHATE (TRIBASIC)	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM PHOSPHATE (TRI-BASIC)	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM PHOSPHITE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM PICRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM POLYSULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM SALICYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM SALTS	23	1	1	1	0	0	0	3	0	0	1	0	1
AMMONIUM SULFAMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM SULFATE	23	1	1	1	4	0	0	4	0	0	1	1	1
AMMONIUM SULFIDE	23	1	3	3	4	0	0	4	1	3	1	0	1
AMMONIUM SULFITE	23	1	0	0	1	0	0	1	0	0	1	0	1
AMMONIUM SULPHATE NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM THIOCYANATE	23	1	1	0	0	0	0	1	0	0	1	0	1
AMMONIUM THIOGLYCOLLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM THIOSULFATE	23	1	1	0	0	0	0	1	0	0	1	0	1
AMMONIUM TUNGSTATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMMONIUM VALERATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMYL ACETATE (BANANA OIL)	23	3	4	4	4	4	0	4	1	1	1	4	1
AMYL ALCOHOL	23	1	2	2	4	4	0	2	1	1	1	4	1
AMYL AMINE	23	4	3	0	0	0	0	4	0	0	1	0	0
AMYL BORATE	23	4	1	1	0	0	0	1	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
AMYL BUTRYATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMYL CHLORIDE (CHLORPENTANE)	23	4	4	1	3	4	0	1	4	1	1	0	1
AMYL CHLORONAPHTHALENE	23	4	4	4	4	4	0	1	0	0	1	4	1
AMYL CINNAMIC ALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMYL LAURATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMYL MERCAPTAN	23	0	0	0	0	0	0	0	0	0	1	0	1
AMYL NAPHTHALENE	23	4	4	4	4	0	0	1	0	0	1	0	1
AMYL NITRATE	23	0	1	0	0	0	0	0	0	0	1	0	1
AMYL NITRITE	23	0	0	0	0	0	0	0	0	0	1	0	1
AMYL PHENOL	23	0	4	0	0	0	0	1	0	0	1	0	1
AMYL PROPIONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
AN-0-3 GRADE M	23	0	0	0	0	0	0	0	0	0	1	0	1
AN-0-366	23	0	0	0	0	0	0	0	0	0	1	0	1
AN-0-6	23	0	0	0	0	0	0	0	0	0	1	0	1
ANDEROL 774	23	0	0	0	0	0	0	1	0	0	1	0	1
ANDEROL L-826	23	0	0	0	0	0	0	0	0	0	1	0	1
ANDEROL L-829	23	0	0	0	0	0	0	0	0	0	1	0	1
ANDEROL® L-774	23	0	0	0	0	0	0	0	0	0	1	0	1
ANG-25 (DIESTER BASE)	23	0	0	0	0	0	0	0	0	0	1	0	1
ANG-25 (GLYCERAL ESTER)	23	0	0	0	0	0	0	0	0	0	1	0	1
ANILINE	23	1	4	0	4	4	1	3	3	3	1	4	1
ANILINE DYES	23	1	4	4	4	3	0	2	0	0	1	4	1
ANILINE HYDROCHLORIDE	23	2	3	3	4	4	0	2	0	0	1	4	1
ANILINE HYDROCHLORINE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANILINE OILS	23	2	4	4	4	0	0	3	0	0	1	0	1
ANILINE SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANILINE SULFITE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANIMAL OILS AND FATS	23	2	1	1	2	0	0	1	0	0	1	0	0
ANISOLE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANISOYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANITIMONY TRIBROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANSUL ETHER (ANESTHETICS)	23	3	3	3	2	4	0	4	0	0	1	2	1
ANSUL ETHER 161 OR 181	23	0	0	0	0	0	0	4	0	0	1	0	1
ANSUL_S ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
ANTHRACENE	23	0	0	0	0	0	0	1	0	0	1	0	1
ANTHRANILIC ACID	23	0	0	0	0	0	0	2	0	0	1	0	1
ANTHRAQUINONE	23	1	0	0	2	0	0	0	0	0	0	0	1
ANTIFREEZE SOLUTIONS	23	0	0	0	0	0	0	2	0	0	1	0	1
ANTIMONY CHLORIDE	23	0	0	0	0	0	0	2	0	0	1	0	1
ANTIMONY PENTACHLORIDE	23	0	4	0	0	0	0	0	0	0	1	0	1
ANTIMONY PENTAFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANTIMONY SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANTIMONY TRICHLORIDE	23	2	1	0	0	0	0	2	0	0	1	0	1
ANTIMONY TRIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ANTIMONY TRIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
AN-VV-0-366B HYDRAULIC	23	0	0	0	0	0	0	0	0	0	1	0	1
AQUA REGIA	23	3	4	4	4	4	0	2	4	4	1	4	1
ARACHIDIC ACID (EICOSANOIC ACID)	23	0	0	0	0	0	0	0	0	0	1	0	1
ARAL VIT AMOL 3865	80	4	1	1	1	4	0	1	1	1	1	1	0
ARAL VIT AMOL 4004	80	4	1	1	1	4	0	1	1	1	1	1	0
ARAL VITAM GX 32	80	4	1	1	1	4	0	1	1	1	1	1	0
ARGON	23	1	3	2	1	3	0	1	1	1	1	0	1
AROCLOR, 1248	23	3	3	3	4	2	0	1	0	0	1	4	1
AROCLOR, 1254	23	3	4	4	4	3	0	1	0	0	1	4	1
AROCLOR, 1260	23	1	1	1	4	2	0	1	0	0	1	4	1
AROMATIC FUELS	23	4	2	2	4	0	0	1	0	0	1	0	1
ARSENIC ACID	23	1	2	1	3	1	0	1	1	3	1	3	1
ARSENIC OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ARSENIC TRICHLORIDE	23	3	2	2	0	0	0	4	0	0	1	0	1
ARSENIC TRIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ARSENIC TRISULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ARSENITES	23	0	0	0	0	0	0	0	0	0	1	0	1
ARSINE	23	0	0	0	0	0	0	0	0	0	1	0	1
ARYL ORTHOSILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ASCORBIC ACID	23	0	0	0	0	0	0	1	0	0	1	0	1
ASKAREL	23	4	2	2	4	4	0	1	0	0	1	4	1
ASPARTIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
ASPHALT	23	4	2	0	2	4	0	1	0	0	1	2	1
ASPHALT / BITUMEN	100	4	3	3	3	4	0	1	1	1	1	1	0
ASPIRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM FLUID	23	4	3	4	4	0	0	1	0	0	1	0	0
ASTM HYDROCARBON TEST FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM METHOD D-471 - 1	23	4	1	1	1	3	0	1	0	0	1	1	1
ASTM METHOD D-471 - 2	23	4	1	1	2	3	0	1	0	0	1	1	1
ASTM METHOD D-471 - 3	23	4	1	1	2	3	0	1	0	0	1	1	1
ASTM OIL NO. 1	23	4	1	1	1	1	0	1	1	1	1	1	1
ASTM OIL NO. 2	23	4	1	1	3	3	0	1	1	1	1	1	1
ASTM OIL NO. 3	23	4	1	1	3	4	0	1	1	1	1	1	1
ASTM OIL NO. 4	23	4	2	2	4	0	0	1	0	0	1	0	1
ASTM OIL NO. 5	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL A	23	4	1	1	1	1	0	1	1	1	1	1	1
ASTM REFERENCE FUEL B	23	4	3	4	3	4	0	1	1	1	1	3	1
ASTM REFERENCE FUEL C	23	4	4	4	3	4	0	1	1	1	1	3	1
ASTM REFERENCE FUEL C/DIPE (25%/75%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/DIPE (85%/15%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/ETBE (25%/75%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/ETBE (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/ETBE (75%/25%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/ETBE (90%/10%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/ETHANOL (90%/10%)	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
- 1 = good, less than 5%
- 2 = moderate, between 5% and 10%
- 3 = not so good, between 10% and 20%
- 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
ASTM REFERENCE FUEL C/METHANOL (15%/85%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/METHANOL (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/METHANOL (75%/25%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/METHANOL (90%/10%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/MOPAR FUEL INJECTOR CLEANER (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/MTBE (25%/75%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/MTBE (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/MTBE (75%/25%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/MTBE (85%/15%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/TAEE (25%/75%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/TAEE (85%/15%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/TAME (25%/75%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL C/TAME (85%/15%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE FUEL D	23	4	4	4	1	4	0	1	1	1	1	1	1
ASTM REFERENCE FUEL H	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE OIL IRM902	23	0	0	0	0	0	0	0	0	0	1	0	1
ASTM REFERENCE OIL IRM903	23	0	0	0	0	0	0	0	0	0	1	0	1
ATREX	23	0	0	0	0	0	0	0	0	0	1	0	1
AUREX 903R	23	0	0	0	0	0	0	0	0	0	1	0	1
AUREX® 256	23	0	0	0	0	0	0	0	0	0	1	0	1
AUTOMATIC TRANSMISSION FLUID (DEXTRON)	23	4	1	1	2	0	0	1	0	0	1	0	1
AUTOMOTIVE BRAKE FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
AUTOMOTIVE FUEL 2B	23	0	0	0	0	0	0	0	0	0	1	0	1
AUTOMOTIVE FUEL 60	23	0	0	0	0	0	0	0	0	0	1	0	1
AUTOMOTIVE FUEL 60B	23	0	0	0	0	0	0	0	0	0	1	0	1
AUTOMOTIVE FUEL RF2	23	0	0	0	0	0	0	0	0	0	1	0	1
AVIATION FUEL	23	4	1	1	1	4	0	1	1	1	1	1	0
AVTAG (SHELL AEROFUEL)	23	0	0	0	0	0	0	0	0	0	1	0	1
AVTEX 903 HYDRAULIC OIL (MIL-H-6083)	23	0	0	0	0	0	0	0	0	0	1	0	1
AXAREL® 9100	23	0	0	0	0	0	0	0	0	0	1	0	1
AZOBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
B.P. AERO HYDRAULIC FLUID NO.1	23	0	0	0	0	0	0	0	0	0	1	0	1
BANANA OIL (AMYL ACETATE)	23	3	4	4	4	4	0	4	0	0	1	4	1
BARDOL B	23	0	0	0	0	0	0	0	0	0	1	0	1
BARIUM CARBONATE	23	1	1	1	0	0	0	1	0	0	1	0	1
BARIUM CHLORATE	23	1	0	0	0	0	0	0	0	0	0	0	1
BARIUM CHLORIDE	23	1	1	1	4	0	0	1	0	3	1	0	1
BARIUM CYANIDE	23	0	3	0	0	0	0	1	0	0	1	0	1
BARIUM HYDRATE	23	1	1	1	4	0	0	1	0	0	1	0	0
BARIUM HYDROXIDE	23	1	1	1	4	1	0	1	1	3	1	4	1
BARIUM IODIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BARIUM NITRATE	23	0	1	0	0	0	0	0	0	0	1	0	1
BARIUM OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BARIUM PEROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
BARIUM POLYSULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BARIUM SALTS	23	1	1	1	1	0	0	1	0	0	1	0	1
BARIUM SULFATE	23	1	1	1	1	1	0	1	0	0	1	1	1
BARIUM SULFIDE	23	1	1	1	1	1	0	1	0	0	1	1	1
BARIUM SULFITE	23	0	0	0	0	0	0	0	0	0	1	0	1
BAYOL 35	23	0	0	0	0	0	0	0	0	0	1	0	1
BAYOL D	23	0	0	0	0	0	0	0	0	0	1	0	1
BEER	23	1	1	1	2	1	0	1	1	1	1	2	1
BEER WORT	90	3	1	1	4	3	0	1	0	0	1	0	0
BEET SUGAR LIQUORS	23	1	1	1	4	1	0	1	0	0	1	4	1
BENZALCHLORIDE	23	4	4	0	4	0	0	1	0	0	1	0	0
BENZALDEHYDE	23	1	4	4	4	3	0	4	3	3	1	4	1
BENZALDEHYDEDISULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZANTHRONE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZENE	23	4	4	4	3	4	3	1	1	1	1	3	1
BENZENE HEXACHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZENE SULFONIC ACID	23	3	4	0	4	4	0	1	0	0	1	4	1
BENZIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZIDINE 3 SULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZIL	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZILIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZINE	23	4	2	3	3	0	0	1	0	0	1	0	1
BENZINE (LIGROIN) (NITROBENZINE) (PET ETHER)	23	4	1	1	2	4	0	1	0	0	1	2	1
BENZOCATECHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZOIC ACID	23	3	3	4	4	3	0	1	3	3	1	4	1
BENZOIN	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZONITRILE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZOPHENONE	23	2	4	4	4	4	0	1	0	0	1	4	1
BENZOQUINONE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZOTRICHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZOTRIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZOYL CHLORIDE	23	4	4	4	4	0	0	2	0	0	1	0	1
BENZOYL PEROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZYL ACETATE	23	0	4	0	0	0	0	4	0	0	1	0	1
BENZYL ALCOHOL	23	3	4	4	4	2	1	1	1	4	1	4	1
BENZYL AMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZYL BENZOATE	23	2	4	4	4	0	0	1	0	0	1	0	1
BENZYL BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZYL BUTYL PHTHALATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZYL CHLORIDE	23	4	4	4	4	4	1	1	1	1	1	4	1
BENZYL PHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
BENZYL SALICYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BERYLLIUM CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BERYLLIUM FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
BERYLLIUM OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BERYLLIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BIOBOR JF (OIL FUNGICIDE)	23	0	0	0	0	0	0	0	0	0	1	0	1
BIOMIL H (HUNGARY)	80	4	4	4	4	4	0	1	1	1	1	1	0
BIPHENYL (DIPHENYL)	23	0	0	0	0	0	0	0	0	0	1	0	1
BIPHENYL (DIPHENYL) (PHENYLBENZENE)	23	4	4	4	4	4	0	1	0	0	1	4	1
BISMUTH CARBONATE	23	1	1	0	0	0	0	1	0	0	1	0	1
BISMUTH NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BISMUTH OXYCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BISULFITE WASTE LIQUOR	23	1	3	3	4	0	0	1	1	3	1	0	0
BITTERN	23	0	0	0	0	0	0	0	0	0	1	0	1
BLACK LIQUOR COLD	23	2	2	0	4	0	0	1	0	0	1	0	0
BLACK POINT 77	23	0	0	0	0	0	0	0	0	0	1	0	1
BLAST FURNACE GAS	23	4	4	4	4	1	0	1	1	1	1	4	1
BLEACH LIQUOR	23	1	4	4	4	3	0	1	4	4	1	0	1
BLEACH SOLUTIONS	23	1	4	2	4	2	1	1	0	0	1	4	1
BONE OIL	23	4	1	0	0	3	0	1	1	1	1	1	1
BORAX	23	1	2	1	1	2	0	1	0	0	1	1	1
BORAX SOLUTION	23	1	1	1	4	3	0	1	1	3	1	3	1
BORDEAUX MIXTURE	23	1	2	0	4	2	0	1	0	0	1	4	1
BORIC ACID	23	1	1	1	3	3	0	1	1	3	1	1	1
BORIC OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORNEOL	23	0	0	0	0	0	0	0	0	0	1	0	1
BORNYL ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORNYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORNYL FORMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORON FLUIDS (HEF)	23	0	0	0	0	0	0	0	0	0	1	0	1
BORON HYDRIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORON PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORON TRIBROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORON TRICHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORON TRIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BORON TRIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BOSCAN ASPHALT (85-100)	23	0	0	0	0	0	0	0	0	0	1	0	1
BP BIOHYD SE 46	80	4	4	4	4	4	0	1	1	1	1	1	0
BP BIOHYD46	80	4	4	4	4	4	0	1	1	1	1	1	0
BP ENERGOL SF-C 15	50	1	1	1	4	3	0	3	1	3	1	2	0
BRAKE FLUID (BASED ON GLYCOL, DOT-4)	100	1	4	4	4	3	0	4	4	4	1	4	0
BRAKE FLUID (BASED ON GLYCOL, DOT-4)	50	1	4	4	4	3	0	4	4	4	1	4	0
BRAKE FLUID (GLYCOL BASED)	23	1	3	3	4	0	0	4	0	0	1	0	0
BRAKE FLUID (MINERAL OIL BASED)	23	4	1	1	1	0	0	1	0	0	1	0	0
BRAKE FLUID (SILICONE OIL BASED)	23	1	3	3	4	0	0	4	0	0	1	0	0
BRAY OIL 762	23	0	0	0	0	0	0	0	0	0	1	0	1
BRAYCO 885 (MIL-L-6085A)	23	0	0	0	0	0	0	0	0	0	1	0	1
BRAYCO 910	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
BRAYCO HYDRAULIC OIL 783 (MIL-H-6083)	23	0	0	0	0	0	0	0	0	0	1	0	1
BRENNTAG TR 32	50	4	1	1	4	1	0	1	1	1	1	3	0
BRENNTAG TR 32	60	4	1	1	4	1	0	1	1	1	1	4	0
BRENNTAG TR 46	50	4	1	1	4	1	0	1	1	1	1	1	0
BRENNTAG TR 46	60	4	1	1	4	1	0	1	1	1	1	3	0
BRINE	23	1	1	1	2	1	0	1	0	0	1	2	1
BROMIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMIDE	23	4	4	0	0	0	0	1	0	0	1	0	0
BROMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMINE HYDROGEN	23	2	4	0	4	0	0	2	0	0	1	0	0
BROMINE HYDROGEN ACID	23	1	4	4	4	0	0	1	0	0	1	0	0
BROMINE PENTAFLUORIDE	23	4	4	4	4	4	0	4	0	0	1	4	1
BROMINE TRIFLUORIDE	23	4	4	4	4	4	0	4	0	0	1	4	1
BROMINE WATER	23	4	4	3	4	4	0	1	4	4	1	4	1
BROMINE, LIQUID	23	4	4	4	4	4	0	1	4	4	1	4	0
BROMO (2-) METHYLPROPANE (2-)	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMO (3-) 1-PROPENE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOBENZENE	23	4	4	4	4	4	0	1	0	0	1	4	1
BROMOBENZENE CYANIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOBUTANE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOCHLOROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOCHLOROPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOCHLOROTRIFLUOROMETHANE(HALOTHANE)	23	4	4	4	4	0	0	1	0	0	1	0	1
BROMOETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOFORM	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOPENTAFLUORIDE	23	4	4	4	4	0	0	4	0	0	0	0	0
BROMOPENTANE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOTOLUENE	23	1	0	0	4	0	0	0	0	0	2	0	0
BROMOTRIFLUORIDE	23	4	4	4	4	0	0	4	0	0	4	0	0
BROMOTRIFLUORMETHANE	23	1	1	1	1	0	0	1	0	0	1	0	0
BROMOTRIFLUOROETHYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
BROMOTRIFLUOROMETHANE (FREON 13B1)	23	0	0	0	0	0	0	0	0	0	1	0	1
BRUCINE SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUFFERED OXIDE ETCHANTS (BOE)	23	0	0	0	0	0	0	0	0	0	1	0	1
BUNKER C (FUEL OIL)	23	0	0	0	0	0	0	0	0	0	1	0	1
BUNKER OIL	23	4	1	1	3	3	0	1	0	0	1	2	1
BUTADIENE (1,3-)	23	1	4	4	4	4	0	2	1	1	1	4	1
BUTANE	23	4	1	1	1	4	0	1	1	1	1	1	1
BUTANEDIAL	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTANEDIOL (1,4-)	23	1	4	0	0	0	0	1	0	0	1	0	1
BUTANETHIOL	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTANOL TERT.	50	3	3	3	4	3	0	1	1	1	1	4	0
BUTANONE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
BUTENE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTTER (ANIMAL FAT)	23	4	1	1	3	2	0	1	0	0	1	1	1
BUTYL ACETATE	23	3	4	4	4	4	4	4	1	1	1	4	1
BUTYL ACETYL RICINOLEATE	23	1	3	2	4	4	0	1	0	0	1	4	1
BUTYL ACRYLATE	23	4	4	4	4	1	0	4	0	0	1	0	1
BUTYL ALCOHOL	23	2	2	1	4	2	1	1	1	1	1	4	1
BUTYL AMINE	23	2	3	3	4	4	0	4	0	0	1	4	1
BUTYL BENZOATE	23	2	4	4	4	0	0	1	0	0	1	0	1
BUTYL BENZOLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL BENZYL PHTHALATE (BBP)	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL BROMIDE	23	0	4	0	0	0	0	2	0	0	1	0	1
BUTYL BUTYRATE	23	1	4	0	0	0	0	1	0	0	1	0	1
BUTYL CARBITOL	23	1	4	4	0	4	0	3	0	0	1	0	1
BUTYL CELLOSOLVE	23	1	3	3	4	0	0	4	0	0	1	4	1
BUTYL CELLOSOLVE ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL CHLORIDE	23	0	4	0	0	0	0	2	0	0	1	0	1
BUTYL ETHER	23	3	3	0	2	0	0	4	0	0	1	0	1
BUTYL GLYCOLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL LACTATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL LAURATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL MERCAPTAN	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL METHRACRYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL OLEATE	23	2	4	4	4	0	0	1	0	0	1	0	1
BUTYL OXALATE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYL PHENOLS	23	4	4	0	4	0	0	1	0	0	1	0	1
BUTYL STEARATE	23	3	2	2	4	0	1	1	0	0	1	0	1
BUTYLAMINE	23	3	3	4	4	3	0	4	0	0	1	4	0
BUTYLBENZOIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYLENE	23	4	2	2	4	4	0	1	1	1	1	4	1
BUTYRALDEHYDE	23	2	4	4	4	4	0	4	0	0	1	4	1
BUTYRIC ACID	23	2	4	4	4	0	0	2	0	0	1	0	1
BUTYRIC ACID ETHYL ESTER	23	1	0	0	0	0	0	0	0	0	3	0	0
BUTYRIC ANHYDRIDE	23	0	3	0	0	0	0	0	0	0	1	0	1
BUTYROLACTONE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYRONITRILE	23	0	0	0	0	0	0	0	0	0	1	0	1
BUTYRYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CADMIUM ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CADMIUM CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CADMIUM CYANIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CADMIUM NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CADMIUM OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CADMIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CADMIUM SULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCINE LIQUORS	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCINING FLUIDS	23	1	1	1	4	0	0	1	0	0	1	0	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
CALCIUM HYPOCHLORITE (AQ)	23	1	2	2	4	2	1	1	0	0	1	4	1
CALCIUM ACETATE	23	2	3	2	4	4	1	4	1	3	1	4	1
CALCIUM ARSENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM BENZOATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM BICARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM BISULFATE	23	1	0	0	0	0	0	0	0	0	1	0	0
CALCIUM BISULFIDE	23	1	0	0	0	0	0	0	0	0	1	0	1
CALCIUM BISULFITE	23	4	4	1	3	1	0	1	0	0	1	1	1
CALCIUM BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM CARBIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM CARBONATE	23	1	1	1	3	0	0	1	0	0	1	0	1
CALCIUM CHLORATE	23	1	1	1	0	0	0	1	0	0	1	0	1
CALCIUM CHLORIDE	23	1	1	1	2	1	1	1	1	3	1	1	1
CALCIUM CHROMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM CYANAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM CYANIDE	23	1	1	1	4	0	0	1	0	0	1	0	1
CALCIUM FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM GLUCONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM HYDRIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM HYDROSULFIDE	23	0	1	0	0	0	0	1	0	0	1	0	1
CALCIUM HYDROXIDE	23	1	1	1	4	4	1	1	1	3	1	1	1
CALCIUM HYPOCHLORIDE	23	1	4	0	4	0	0	1	0	0	1	0	0
CALCIUM HYPOCHLORITE	23	1	3	3	4	3	0	1	1	3	1	3	1
CALCIUM HYPOPHOSPHITE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM LACTATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM MAGNESIUM ACETATE SOLUTION (20%)	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM NAPHTHENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM NITRATE	23	1	1	1	1	2	1	1	0	0	1	1	1
CALCIUM OXALATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM OXICHLORIDE	23	2	2	0	4	0	0	1	0	0	1	0	0
CALCIUM OXIDE	23	1	1	0	0	0	0	0	0	0	1	0	1
CALCIUM PERMANGANATE	23	1	0	0	0	0	0	0	0	0	1	0	1
CALCIUM PEROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM PHENOLSULPHONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM PHOSPHATE	23	1	1	1	3	1	0	1	1	3	1	1	1
CALCIUM PHOSPHATE, MONOBASIC	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM PROPIONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM PYRIDINE SULFONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM SALTS	23	1	1	1	1	0	0	1	0	0	1	0	1
CALCIUM SILICATE	23	1	1	1	0	0	0	1	0	0	1	0	1
CALCIUM STEARATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM SULFAMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM SULFATE (CEMENT)	23	1	1	1	0	0	0	1	0	0	1	0	1
CALCIUM SULFIDE	23	1	2	1	1	2	1	1	0	0	1	1	1
CALCIUM SULFITE	23	1	1	1	1	0	0	1	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
CALCIUM THIOCYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALCIUM THIOSULFATE	23	1	2	2	3	0	0	1	0	0	1	0	1
CALCIUM TUNGSTATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALICHE	23	0	0	0	0	0	0	0	0	0	1	0	1
CALICHE LIQUORS	23	1	1	1	1	0	0	1	0	0	1	0	1
CAMPHENE	23	4	1	0	0	0	0	2	0	0	1	0	1
CAMPHOR OIL	23	4	1	1	3	4	0	1	1	1	1	1	1
CAMPHORIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CANE SUGAR LIQUORS	23	1	2	2	4	1	0	1	0	0	1	4	1
CAPRIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CAPROIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CAPROIC ALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CAPROLACTAM	23	0	0	0	0	0	0	0	0	0	1	0	1
CAPRONALDEHYDE	23	2	4	0	4	0	0	4	0	0	1	0	1
CAPRYLIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CARBAMATE	23	2	3	0	4	0	0	1	0	0	1	4	1
CARBAZOLE	23	0	0	0	0	0	0	0	0	0	1	0	1
CARBITOL®	23	2	2	0	4	0	0	2	0	0	1	0	1
CARBOLIC ACID	23	4	4	4	4	4	0	1	0	0	1	4	1
CARBON BISULFIDE	23	4	3	4	0	4	1	1	0	0	1	0	1
CARBON DIOXIDE	23	2	1	1	1	2	0	1	0	0	1	1	1
CARBON DIOXIDE, DRY	23	3	1	1	1	3	0	2	1	0	1	1	1
CARBON DIOXIDE, WET	23	3	1	1	3	3	0	2	0	0	1	1	1
CARBON DISULFIDE	23	4	4	2	4	4	0	1	1	0	1	4	1
CARBON FLUORIDES	23	0	0	0	0	0	0	0	0	0	1	0	1
CARBON MONOXIDE	23	2	1	1	1	1	0	1	1	1	1	1	1
CARBON TETRABROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CARBON TETRACHLORIDE	23	4	3	2	4	4	4	1	0	0	1	4	1
CARBON TETRAFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CARBONIC ACID	23	1	2	1	3	1	0	1	1	1	1	1	1
CARBONYL SULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CASEIN	23	0	0	0	0	0	0	0	0	0	1	0	1
CASTOR OIL	23	3	1	1	1	1	1	1	0	0	1	1	1
CASTROL ALPHA SP 68	80	4	1	1	1	3	0	1	1	1	1	1	0
CASTROL BIOTEC ALPIN 22	80	4	4	4	3	4	0	1	1	1	1	1	0
CASTROL BIOTEC HVX	80	4	4	4	3	4	0	1	1	1	1	1	0
CASTROL HYSPIAN AWS 32	80	4	1	1	1	4	0	1	1	1	1	1	0
CATALENE (ISOPROPYL NITRATE)	23	0	0	0	0	0	0	0	0	0	1	0	1
CAUSTIC LIME	23	0	0	0	0	0	0	0	0	0	1	0	1
CAUSTIC POTASH	23	1	2	0	2	0	0	2	0	0	1	0	1
CELLOSOLVE	23	2	4	4	4	4	0	3	0	0	1	4	1
CELLOSOLVE ACETATE	23	2	4	4	4	4	0	4	0	0	1	4	1
CELLUGUARD	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULOSE ACETATE	23	2	4	4	0	0	0	4	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
CELLULOSE ACETATE BUTYRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULOSE ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULOSE NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULOSE TRIPROPIONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULUBE (FRYQUEL)	23	1	4	4	4	1	0	1	0	0	1	4	1
CELLULUBE (PHOSPHATE ESTERS)	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULUBE 220	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULUBE 550A	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULUBE A60	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLULUBE®	23	0	0	0	0	0	0	0	0	0	1	0	1
CELLUTHERM 2505A	23	0	0	0	0	0	0	0	0	0	1	0	1
CEMENT, POTLAND	23	0	0	0	0	0	0	0	0	0	1	0	1
CENWAX E	23	0	0	0	0	0	0	0	0	0	1	0	1
CERIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CEROUS CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CEROUS FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CEROUS NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CETANE	23	4	1	1	4	4	0	1	0	0	1	0	1
CETANE (HEXADECANE)	23	0	0	0	0	0	0	0	0	0	1	0	1
CETYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
CHAULMOGRIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CHINA WOOD OIL	23	3	1	1	3	4	0	1	0	0	1	3	1
CHLORACETIC ACID	23	2	4	4	4	4	0	4	4	4	1	4	0
CHLORAL	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORAL (TRICHLOROACETALDEHYDE)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORAL HYDRATE	23	3	4	0	0	0	0	3	0	0	1	0	0
CHLORAMINE	23	1	1	1	0	0	0	0	0	0	1	0	1
CHLORANTHRAQUINONE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORBUTADIENE	23	4	4	4	4	4	0	1	0	0	1	4	0
CHLORDANE	23	4	2	2	0	0	0	1	0	0	1	0	1
CHLOREXTOL	23	4	2	2	4	0	0	1	0	0	1	0	1
CHLORIC ACID	23	1	0	0	4	0	0	0	0	0	1	0	1
CHLORINATED LIME	23	2	2	0	4	0	0	1	0	0	1	0	0
CHLORINATED NAPHTHALENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORINATED SALT BRINE	23	4	4	4	4	0	0	1	0	0	1	0	1
CHLORINATED SOLVENTS	23	4	4	4	4	0	0	1	0	0	1	0	1
CHLORINE (DRY)	23	4	4	3	4	4	0	1	4	4	1	4	1
CHLORINE (WET)	23	3	4	3	4	4	0	2	4	4	1	4	1
CHLORINE DIOXIDE	23	3	4	4	4	0	0	1	0	0	1	4	1
CHLORINE TRIFLUORIDE	23	4	4	4	4	4	0	4	0	0	1	4	1
CHLORINE WATER	23	3	4	4	4	4	0	4	4	4	1	4	1
CHLORO (1-) METHYLPROPANE (2-)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORO (2-) METHYLBUTANE (2-)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORO OXYFLUORIDES	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORO XYLENOLS	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
CHLORO-,1-NITRO ETHANE, (1-)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROACETALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROACETIC ACID	23	1	4	4	4	0	0	4	0	0	1	4	1
CHLOROACETONE	23	1	4	4	4	4	0	4	0	0	1	4	1
CHLOROACETYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROAMINO BENZOIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBENZALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBENZENE	23	4	4	4	4	4	0	1	0	0	1	4	1
CHLOROBENZENE CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBENZENE TRIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBENZOCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBENZOTRIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBROMO METHANE	23	2	4	4	4	0	0	1	0	0	1	0	1
CHLOROBROMO PROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBROMOMETHANE	23	2	4	4	4	4	0	1	0	0	1	4	1
CHLOROBROMOPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBUTADIENE	23	4	4	4	4	4	0	1	0	0	1	4	1
CHLOROBUTADIENE (CHLOROPRENE)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBUTANE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROBUTANE (BUTYL CHLORIDE)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORODIFLUOROETHANE (FREON 142B)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORODIFLUOROMETHANE (FREON 22)	23	1	4	0	4	0	0	4	0	0	1	0	1
CHLORODODECANE	23	4	4	4	4	4	0	1	0	0	1	4	1
CHLOROETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROETHANE SULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROETHENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROETHYLBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROFLUOROMETHANE (F-22)	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROFORM	23	4	4	4	4	4	4	1	4	4	1	4	1
CHLOROHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORONAPHTHALENE	23	4	4	0	0	0	0	1	0	0	1	0	0
CHLORONITROBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLORONITROETHANE	23	4	4	4	4	4	0	4	0	0	3	4	1
CHLOROPENTAFLUOROETHANE (FREON 115)	23	1	1	0	1	0	0	1	0	0	2	0	1
CHLOROPENTANE	23	4	4	1	3	0	0	1	0	0	1	0	1
CHLOROPHENOL	23	4	4	4	4	4	0	1	0	0	1	4	1
CHLOROPICRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROPRENE	23	4	4	4	4	0	0	1	0	0	1	0	1
CHLOROPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROPROPENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROSILANES	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROSULFONIC ACID	23	4	4	4	4	4	1	4	0	0	1	4	1
CHLOROTOLUENE	23	4	4	4	4	4	0	1	0	0	1	4	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
CHLOROTOLUENE SULFONIC ACID	23	4	4	4	4	0	0	4	0	0	1	0	1
CHLOROTOLUIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROTRIFLUORIDE	23	4	4	4	4	0	0	4	0	0	4	0	1
CHLOROTRIFLUOROETHYLENE (CTFE)	23	0	4	0	0	0	0	0	0	0	1	0	1
CHLOROTRIFLUOROMETHANE (FREON 13)	23	1	1	1	4	0	0	3	0	0	1	0	1
CHLOROXYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHLOROXYLOLS	23	0	0	0	0	0	0	0	0	0	1	0	1
CHOLESTEROL	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROME ALUM	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROME PLATING SOLUTIONS	23	2	4	4	4	3	0	1	4	4	1	4	1
CHROMIC ACID	23	3	4	4	4	3	1	1	4	4	1	4	1
CHROMIC CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROMIC FLUORIDES	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROMIC HYDROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROMIC NITRATES	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROMIC OXIDE(DILUTED)	23	2	4	4	4	0	0	1	0	0	1	0	1
CHROMIC PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROMIC SULFATE	23	2	2	2	0	0	0	1	0	0	1	0	1
CHROMIUM POTASSIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CHROMIUM-POTASSIUM ALUM, AQ. SOL.	50	1	1	1	4	1	0	1	0	0	1	0	0
CHROMYL CHLORIDES	23	0	0	0	0	0	0	0	0	0	1	0	1
CHX-604 (HYDRAULIC FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
CICO H 3000	80	4	4	3	4	4	0	1	1	1	1	1	0
CINNAMIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CINNAMIC ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
CINNAMIC ALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CIRCO LIGHT PROCESS OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
CITIES XPA-1668 ATF	23	0	0	0	0	0	0	0	0	0	1	0	1
CITRIC ACID	23	1	1	1	3	1	1	1	1	3	1	1	1
CITY SERVICE 65, 120, 250	23	0	0	0	0	0	0	0	0	0	1	0	1
CITY SERVICE KOOL MOTOR OIL NO.140	23	0	0	0	0	0	0	0	0	0	1	0	1
CITY SERVICE PACEMAKER NO.2	23	0	0	0	0	0	0	0	0	0	1	0	1
COAL GAS	23	1	4	4	4	0	0	1	0	0	1	3	0
COAL TAR	23	0	0	0	0	0	0	0	0	0	1	0	1
COAL TAR (CREOSOTE)	23	4	1	0	3	4	0	1	0	0	1	3	1
COBALT CHLORIDE	23	1	1	1	3	3	0	1	1	3	1	0	1
COBALTOUS ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COBALTOUS BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
COBALTOUS LINOLEATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COBALTOUS NAPHTHENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COBALTOUS SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COCA-COLA		1	3	3	0	1	0	4	0	0	1	0	0
COCONUT FATTY ACID	80	4	1	1	3	1	0	1	1	1	1	0	0
COCONUT OIL	23	3	1	1	2	1	0	1	1	1	1	2	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
COCONUT OIL	80	3	1	1	3	1	0	1	1	1	1	2	0
COD LIVER OIL	23	1	3	3	1	2	0	1	1	1	1	1	1
CODEINE	23	0	0	0	0	0	0	0	0	0	1	0	1
COFFEE	50	1	2	2	4	1	0	1	1	3	1	1	0
COKE OVEN GAS	23	4	4	4	4	2	0	1	0	0	1	4	1
COLOPHONY	23	1	0	0	0	0	0	0	0	0	0	0	0
COOLANOL	23	4	1	1	4	0	0	1	0	0	1	0	1
COPPER ACETATE	23	1	2	2	4	4	0	4	1	3	1	4	1
COPPER AMMONIUM ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COPPER CARBONATE	23	0	1	1	0	0	0	1	0	0	1	0	1
COPPER CHLORIDE	23	1	1	1	3	1	0	1	1	3	1	1	1
COPPER CYANIDE	23	1	1	1	1	1	0	1	0	0	1	1	1
COPPER GLUCONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COPPER NAPHTHENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COPPER NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
COPPER OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
COPPER SALT	23	0	0	0	0	0	0	0	0	0	1	0	1
COPPER SALTS	23	1	1	1	1	0	0	1	0	0	1	0	1
COPPER SULFATE	23	1	1	1	3	1	0	1	1	1	1	2	1
COPPER SULFIDE	23	0	1	0	0	0	0	1	0	0	1	0	0
CORN OIL	23	3	1	1	1	1	0	1	0	0	1	1	1
CORN SYRUP	23	0	0	0	0	0	0	0	0	0	1	0	1
COTTAGE CHEESE 60%	50	1	1	1	3	1	0	1	0	0	1	0	0
COTTONSEED OIL	23	2	1	1	1	3	1	1	1	1	1	1	1
CREAM 30%	50	1	1	1	0	1	0	1	1	0	1	1	0
CREOSOLS	23	4	4	4	4	4	0	1	0	0	1	4	0
CREOSOTE	23	0	0	0	0	0	0	0	0	0	1	0	1
CREOSOTE (COAL TAR)	23	4	1	1	3	4	0	1	0	0	1	3	1
CREOSOTE (WOOD TAR)		4	1	2	3	0	0	1	0	0	1	0	0
CREOSOTE OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
CRESOL (CRESYLIC ACID)		4	4	2	4	0	0	1	0	0	1	0	0
CRESOL (METHYL PHENOL)	23	4	4	0	4	4	1	1	0	0	1	4	1
CRESOL (O-CRESOL)	70	4	4	4	4	4	0	1	0	4	1	4	0
CRESYLIC ACID	23	4	4	1	4	4	1	1	0	0	1	4	1
CROTONALDEHYDE	23	2	2	0	0	0	0	2	0	0	1	0	1
CROTONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CRUDE OIL	23	4	1	1	2	3	0	1	1	1	1	1	1
CRUDE OIL - AROMATIC BASE	80	4	1	1	3	4	0	1	1	1	1	1	0
CRUDE OIL - PARAFFIN BASE	80	4	1	1	3	4	0	1	1	1	1	1	0
CUMENE	23	4	4	4	4	4	0	1	0	0	1	4	1
CUMENE HYDROPEROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CUMINALDEHYDE (CUMALDEHYD)	23	0	0	0	0	0	0	0	0	0	1	0	1
CUPRIC SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CUTTING OIL	23	4	1	1	1	0	0	1	0	0	1	0	1
CYANAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
CYANIDES	23	0	0	0	0	0	0	0	0	0	1	0	1
CYANOACETIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
CYANOGEN CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYANOGEN GAS	23	0	0	0	0	0	0	0	0	0	1	0	1
CYANOHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
CYANURIC CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOHEXANE	23	4	1	1	1	4	2	1	1	1	1	1	1
CYCLOHEXANOL	23	3	3	1	4	4	0	1	0	0	1	4	1
CYCLOHEXANONE	23	2	4	4	4	4	2	4	1	1	1	4	1
CYCLOHEXENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOHEXYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOHEXYLAMINE CARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOHEXYLAMINE LAURATE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOPENTADIENE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOPENTANE	23	4	4	0	0	0	0	1	0	0	1	0	1
CYCLOPENTANONE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOPOLYOLEFINS	23	0	0	0	0	0	0	0	0	0	1	0	1
CYCLOPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
CYMENE	23	4	4	4	4	0	0	1	0	0	1	0	1
D.P. 47	23	0	0	0	0	0	0	0	0	0	1	0	1
DBE (DIBASIC ESTERS)	23	0	0	0	0	0	0	0	0	0	1	0	1
DC-200 SILICONE OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
DDT (DICHLORODIPHENYLTRICHLOROETHANE)	23	0	0	0	0	0	0	0	0	0	1	0	1
DECALIN (DECAHYDRONAPHTALENE)	23	4	4	4	4	4	0	1	1	1	1	0	0
DECANALE	23	4	4	0	0	0	0	4	0	0	1	0	0
DECANE	23	4	1	1	2	2	0	1	0	0	1	2	1
DECANOL (10-phenyl-1-decanol)	23	0	1	0	0	0	0	2	0	0	1	0	1
DECYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
DEIONIZED WATER (UDPI)	23	0	0	0	0	0	0	0	0	0	1	0	1
DENATURED ALCOHOL	23	1	2	2	4	1	0	1	0	0	1	4	1
DETERGENT BLEACH SOLUTIONS (1%)	23	0	0	0	0	0	0	0	0	0	1	0	1
DETERGENT SOLUTIONS	23	1	1	1	4	1	0	1	0	0	1	4	1
DEUTERIUM	23	0	0	0	0	0	0	0	0	0	1	0	1
DEVELOPING FLUIDS	23	2	1	1	0	1	0	1	0	0	1	0	1
DEXRON ATF	23	0	0	0	0	0	0	0	0	0	1	0	1
DEXRON ATF (KENDALE)	23	0	0	0	0	0	0	0	0	0	1	0	1
DEXRON ATF (QUAKER STATE)	23	0	0	0	0	0	0	0	0	0	1	0	1
DEXRON ATF (TEXACO)	23	0	0	0	0	0	0	0	0	0	1	0	1
DEXTRAN	23	0	0	0	0	0	0	0	0	0	1	0	1
DEXTRIN	23	1	1	1	1	1	0	1	1	1	1	1	1
DEXTRO LACTIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
DEXTROSE	23	1	1	1	4	0	0	1	0	0	1	0	1
DI(2-ETHYLHEXYL) PHTHALATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIACETONE ALCOHOL (DIACETOL)	23	1	4	4	4	0	0	4	0	0	1	0	1
DIALLYL AMINE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
DIALLYL ETHER	23	0	0	0	0	0	0	0	0	0	0	0	0
DIALLYL PHTHALATE (DAP)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIAMYLAMINE (ALLYLAMINE)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIAZINON	23	4	3	0	0	0	0	2	0	0	1	0	1
DIAZOBICYCLOUNDECAN	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBENZYL (SYM-DIPHENYLETHANE)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBENZYL ETHER	23	3	4	4	3	3	0	4	0	0	1	2	1
DIBENZYL KETONE (1,3-diphenylacetone)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBENZYL SEBACATE	23	2	4	4	2	4	0	2	0	0	1	0	1
DIBORANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBROMOETHANE	23	0	0	0	0	0	0	0	0	0	0	0	0
DIBROMOETHYLBENZENE (ALKAZENE)	23	4	4	4	4	4	0	2	0	0	1	4	1
DIBROMOMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBROMOPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBROMOTETRAFLUOROETHANE (FREON 114B2)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBUTYL AMINE	23	3	4	4	4	3	0	4	0	0	1	4	1
DIBUTYL CELLOSOLVE® ADIPATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBUTYL ETHER	23	3	4	4	2	4	0	3	0	0	1	2	1
DIBUTYL METHYLENEDITHIOGLYCOLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBUTYL PHTHALATE (DBP)	23	2	4	4	3	3	0	3	0	0	1	0	1
DIBUTYL SEBACATE (DBS)	23	2	4	4	4	3	0	2	1	0	1	4	1
DIBUTYL THIOGLYCOLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIBUTYL THIOUREA	23	0	0	0	0	0	0	0	0	0	1	0	1
DICAPRYL PHTHALATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROACETIC ACID	23	1	0	0	2	0	0	0	0	0	4	0	1
DICHLOROANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROBENZENE	23	4	4	4	4	4	0	2	3	1	1	4	0
DICHLOROBUTANE	23	4	2	2	4	0	0	1	0	0	1	0	1
DICHLOROBUTENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLORODIFLUOROMETHANE (FREON 12)	23	2	1	1	2	0	0	2	0	0	1	0	1
DICHLORODIPHENYL DICHLOROETHANE (DDD)	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLORODIPHENYLTRICHLOROETHANE (DDT)	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROETHYLENE	23	4	4	4	4	4	0	1	1	4	2	4	1
DICHLOROETHYLEETHER	23	1	0	0	4	0	0	0	0	0	0	0	0
DICHLOROFLUOROETHANE (F-141B)	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROFLUOROMETHANE (FREON 21)	23	2	4	4	4	0	0	4	0	0	4	0	1
DICHLOROHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROISOPROPYL ETHER	23	3	4	4	2	0	0	3	0	0	1	0	1
DICHLOROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROMETHYL ACETATE	23	4	4	4	4	4	0	4	0	0	1	4	0
DICHLOROPENTANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROPHENOL (2, 4-)	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROPHENOXYACETIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
DICHLOROPROPENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROSILANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLOROTETRAFLUOROETHANE (FREON 114)	23	2	1	2	1	0	0	1	0	0	2	0	1
DICHLOROTRIFLUOROETHANE (F-123)	23	0	0	0	0	0	0	0	0	0	1	0	1
DICHLORPROP	23	0	0	0	0	0	0	0	0	0	1	0	1
DICYCLOHEXYL AMMONIUM NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DICYCLOHEXYLAMINE	23	4	3	3	4	4	0	4	0	0	1	4	1
DICYCLOPENTADIENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIELDRIN (HEOD)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIESEL OIL	23	4	1	1	3	4	2	1	1	1	1	3	1
DIESTER LUBRICANT (MIL-L-7808)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIESTER SYNTHETIC LUBRICATING OILS	23	0	0	0	0	0	0	0	0	0	1	0	1
DIETHANOLAMINE (DEA)	23	1	0	0	2	0	0	0	0	0	0	0	1
DIETHYL BENZENE	23	4	4	0	4	4	0	1	0	0	1	4	1
DIETHYL CARBONATE	23	1	0	0	0	0	0	0	0	0	0	0	1
DIETHYL ETHER	23	4	4	4	3	4	0	4	0	0	1	1	1
DIETHYL PHTHALATE	23	1	0	0	4	0	0	0	0	0	3	0	1
DIETHYL SEBACATE	23	2	2	3	4	2	0	2	0	0	1	4	1
DIETHYL SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIETHYLAMINE	23	2	4	4	3	2	0	4	1	0	1	3	1
DIETHYLANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIETHYLBENZENE	23	1	0	2	4	0	0	0	0	0	1	0	1
DIETHYLENE GLYCOL	23	1	1	1	4	3	0	1	0	0	1	4	1
DIETHYLENE GLYCOL BUTYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
DIETHYLENE GLYCOL METHYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
DIETHYLENETRIAMINE	23	1	0	0	0	0	0	0	0	0	0	0	1
DIFLUOROBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIFLUORODIBROMOMETHANE	23	1	4	4	4	0	0	0	0	0	0	0	1
DIFLUORODICHLOROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIFLUOROETHANE (FREON 152A)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIFLUOROETHYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIFLUOROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIFLUOROMONOCHELOROETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIGLYCOL CHLOROFORMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIGLYCOLIC ACID, AQ. SOL.	50	1	3	3	4	0	0	1	0	3	1	4	1
DIHYDROXYDIPHENYL SULFONE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIISOBUTYL KETONE	23	1	4	4	4	4	0	4	0	0	4	4	1
DIISOBUTYLCARBINOL	23	0	0	0	0	0	0	0	0	0	1	0	1
DIISOBUTYLENE	23	4	4	3	4	4	0	1	0	0	1	4	1
DIISODECYLADIPATE (DIDA)	23	1	0	0	4	0	0	0	0	0	3	0	0
DIISODECYLPHTALATE	23	1	0	0	4	0	0	0	0	0	3	0	0
DIISOOCTYL ADIPATE (DIOA)	23	1	0	0	4	0	0	0	0	0	3	0	0
DIISOOCTYL PHTALATE (DIOP)	23	1	0	0	4	0	0	0	0	0	3	0	0
DIISOOCTYL SEBACATE (DISO)	23	1	4	3	4	0	0	4	0	0	2	0	1
DIISOPROPYL AMINE	23	0	0	0	2	0	0	0	0	0	0	0	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
DIISOPROPYL BENZENE	23	1	4	2	4	0	0	4	0	0	1	0	1
DIISOPROPYL ETHER (DIPE)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIISOPROPYL KETONE	23	1	4	4	4	4	0	4	0	0	1	4	1
DIISOPROPYLIDENE ACETONE (PHORONE)	23	3	4	0	4	4	0	4	0	0	1	4	1
DIKETENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL ACETAMIDE (DMAC)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL AMINE (DMA)	23	3	4	4	4	4	0	4	1	0	1	4	0
DIMETHYL ANILINE	23	2	4	4	4	4	0	4	0	0	1	4	0
DIMETHYL BUTANE	n.a.	4	1	1	0	4	0	1	0	0	1	0	0
DIMETHYL DISULFIDE (DMDS)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL ETHER	23	1	4	4	4	4	0	4	1	0	1	4	1
DIMETHYL FORMALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL FORMAMIDE (DMF)	23	2	4	4	4	3	0	4	1	1	1	4	1
DIMETHYL HEPTANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL HYDRAZINE	23	1	3	3	4	4	0	4	0	0	1	4	1
DIMETHYL PHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL PHENYL CARBINOL	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL PHENYL METHANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL PHTHALATE	23	2	4	4	4	4	0	2	0	0	1	4	1
DIMETHYL SULFATE	23	0	0	0	4	0	0	0	0	0	2	0	0
DIMETHYL SULFIDE	23	0	0	0	4	0	0	0	0	0	0	0	0
DIMETHYL SULFOXIDE (DMSO)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIMETHYL TEREPHTHALATE (DMT)	23	0	0	0	0	0	0	0	0	0	1	0	1
DINITROBENZENE (DNB)	23	0	0	0	0	0	0	0	0	0	1	0	1
DINITROCHLOROBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DINITROGEN TETROXIDE	23	3	4	4	4	0	0	4	0	0	1	0	1
DINITROTOLUENE (DNT)	23	4	4	4	4	0	0	3	0	0	1	0	1
DIOCTYL PHTHALATE (DOP)	23	1	4	4	3	4	0	1	1	1	1	4	0
DIOCTYL SEBACATE (DOS)	23	2	4	4	2	4	0	2	0	0	1	4	0
DIOCTYL SEBECATE	23	2	4	4	2	3	1	2	0	0	1	2	1
DIOCTYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIOXANE	23	2	4	3	4	4	4	4	1	1	1	4	1
DIOXOLANE	23	2	4	4	4	4	0	4	0	0	1	4	1
DIPE (DIISOPROPYL ETHER)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIPENTENE	23	4	2	2	4	4	0	1	0	0	1	4	1
DIPHENYL	23	0	0	0	0	0	0	0	0	0	1	0	1
DIPHENYL (BIPHENOL)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIPHENYL (BIPHENYL) (PHENYLBENZENE)	23	4	4	4	4	4	2	1	0	0	1	4	1
DIPHENYL ETHER (DIPHENYL OXIDE)	23	4	4	4	4	4	0	1	1	1	1	4	1
DIPHENYL PROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIPHENYLAMINE (DPA)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIPHENYLENE OXIDE (DIBENZOFURAN)	23	0	0	0	0	0	0	0	0	0	1	0	1
DIPHENYLPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIPROPYL AMINE	23	1	0	0	2	0	0	0	0	0	0	0	0
DIPROPYLEN GLYCOL	23	1	0	0	1	0	0	0	0	0	1	0	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
DISILANE	23	0	0	0	0	0	0	0	0	0	1	0	1
DI-TERT-BUTYL PEROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
DIVINYLBENZOL (DVB)	23	4	4	0	3	0	0	2	0	0	1	0	1
DODECYL ALCOHOL	23	1	1	1	4	0	0	1	0	0	1	0	1
DODECYLBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
DOW CHEMICAL 50-4, ET588	23	0	0	0	0	0	0	0	0	0	1	0	1
DOW CORNING 1208, 4050, 6620, F-60, XF-60	23	0	0	0	0	0	0	0	0	0	1	0	1
DOW CORNING 3, 4, 11	23	0	0	0	0	0	0	0	0	0	1	0	1
DOW CORNING 5, 33, 44, 200, 220, 510, 550, 705, 710	23	0	0	0	0	0	0	0	0	0	1	0	1
DOW CORNING 55	23	0	0	0	0	0	0	0	0	0	1	0	1
DOW CORNING 550 E	80	4	4	4	4	4	0	1	1	1	1	1	0
DOW CORNING F-61	23	0	0	0	0	0	0	0	0	0	1	0	1
DOW GUARD	23	0	0	0	0	0	0	0	0	0	1	0	1
DOWANOL® P MIX	23	0	0	0	0	0	0	0	0	0	1	0	1
DOWTHERM 209	23	0	0	0	0	0	0	0	0	0	1	0	1
DOWTHERM 209/WATER (54%/46%)	23	0	0	0	0	0	0	0	0	0	1	0	1
DOWTHERM OIL	23	4	4	4	3	3	0	1	0	0	1	3	1
DRINKING WATER	23	0	0	0	0	0	0	0	0	0	1	0	1
DRY CLEANING FLUIDS	23	4	3	3	4	4	0	1	0	0	1	4	1
DTE LIGHT OIL	23	4	1	1	2	0	0	1	0	0	1	0	1
DURAD EHB	23	0	0	0	0	0	0	0	0	0	1	0	1
DV-4079	23	0	0	0	0	0	0	0	0	0	1	0	1
DYMEL® 142	23	0	0	0	0	0	0	0	0	0	1	0	1
DYMEL® 152	23	0	0	0	0	0	0	0	0	0	1	0	1
DYMEL® 22	23	0	0	0	0	0	0	0	0	0	1	0	1
DYMEL® A	23	0	0	0	0	0	0	0	0	0	1	0	1
EKC265™	23	0	0	0	0	0	0	0	0	0	1	0	1
EKC4000PCT™	23	0	0	0	0	0	0	0	0	0	1	0	1
EKC830™	23	0	0	0	0	0	0	0	0	0	1	0	1
ELCO 28 EP LUBRICANT	23	0	0	0	0	0	0	0	0	0	1	0	1
ELCO L-14374	23	0	0	0	0	0	0	0	0	0	1	0	1
ELCO M2C-105A	23	0	0	0	0	0	0	0	0	0	1	0	1
ELCO M2C-108A	23	0	0	0	0	0	0	0	0	0	1	0	1
ELCO M2C-111A	23	0	0	0	0	0	0	0	0	0	1	0	1
ELCO M2C-119A	23	0	0	0	0	0	0	0	0	0	1	0	1
ELECTROPLATING BATH (CHROME)	n.a.	1	0	0	0	4	0	1	4	4	1	0	0
ELECTROPLATING BATH (NOT CHROME)	n.a.	1	1	0	0	4	0	1	4	4	1	0	0
EPICHLOROHYDRIN	23	2	4	4	4	4	0	4	0	0	1	4	1
EPOXY RESINS	23	1	3	0	0	0	0	4	0	0	1	0	1
ERIFON HD 856	140	2	1	1	4	2	0	3	1	3	1	1	0
ERUCIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
ESAM-6 FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSO 20W50 OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSO AVIATION NO.100 OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSO CAZAR K1(MINERAL-GREASE)	80	4	1	1	1	4	0	1	1	1	1	1	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
ESSO ESSTIC 42, 43	23	4	1	1	3	4	0	1	1	1	1	1	0
ESSO FUEL 208	23	4	1	1	4	4	0	1	0	0	1	0	0
ESSO GOLDEN GASOLINE	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSO MOTOR OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSO NUTO H 22	80	4	1	1	1	4	0	1	1	1	1	1	0
ESSO NUTO H 68	80	4	1	1	1	3	0	1	1	1	1	1	0
ESSO SPINASSO 10	80	4	1	1	1	4	0	1	1	1	1	1	0
ESSO THERMALOIL T	200	4	4	4	4	4	0	1	4	4	1	4	0
ESSO TRANSMISSION FLUID, TYPE A	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSO WS812 (MIL-L-7808A)	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSO XP90-EP LUBRICANT	23	0	0	0	0	0	0	0	0	0	1	0	1
ESSTIC 42, 43	23	0	0	0	0	0	0	0	0	0	1	0	1
ETBE (ETHYL TERT-BUTYL ETHER)	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHANE	23	4	1	1	3	4	0	1	1	1	1	3	1
ETHANETHIOL	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHANOL	23	1	2	1	4	4	1	3	1	2	1	4	1
ETHANOLAMINE	23	2	3	3	3	3	1	4	0	0	1	3	1
ETHER	23	3	3	3	3	4	0	3	0	0	1	3	0
ETHOXYETHYL ACETATE (EGMEEA)	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHY CHLOROFORMATE	23	2	4	0	4	4	0	4	0	0	1	4	1
ETHYL ACETATE	23	2	4	4	4	2	4	4	1	1	1	4	1
ETHYL ACETOACETATE	23	2	4	0	4	2	0	4	0	0	1	4	1
ETHYL ACRYLATE	23	2	4	4	4	2	0	4	1	1	1	4	1
ETHYL ACRYLIC ACID	23	1	4	4	4	0	0	0	0	0	0	0	1
ETHYL ALUMINUM DICHLORIDE	23	1	0	0	4	0	0	0	0	0	2	0	1
ETHYL AMINE	23	1	0	0	3	0	0	0	0	0	4	0	1
ETHYL BENZENE	23	4	4	4	4	4	2	1	0	0	1	4	1
ETHYL BENZOATE	23	4	4	4	4	4	3	1	0	0	1	4	0
ETHYL BROMIDE	23	4	2	2	3	0	0	1	0	0	1	0	0
ETHYL BUTYL ACETATE	23	1	0	0	4	0	0	0	0	0	4	0	0
ETHYL BUTYL ALOCOHOL	23	1	4	1	1	0	0	0	0	0	1	0	0
ETHYL BUTYL KETONE	23	1	0	0	4	0	0	0	0	0	4	0	0
ETHYL BUTYRALDEHYD	23	1	0	0	4	0	0	0	0	0	4	0	0
ETHYL BUTYRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL CELLOSOLVE	23	4	4	4	4	4	0	4	0	0	1	4	1
ETHYL CELLULOSE	23	2	4	4	2	3	0	4	0	0	1	2	1
ETHYL CHLORIDE	23	3	1	0	2	4	0	1	1	1	1	2	1
ETHYL CHLOROCARBONATE	23	4	4	4	4	4	0	1	0	0	1	4	1
ETHYL CHLOROFORMATE	23	4	4	0	4	0	0	1	0	0	1	0	1
ETHYL CYANIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL CYCLOPENTANE	23	4	1	1	1	0	0	1	0	0	1	0	1
ETHYL ETHER	23	4	4	4	3	4	0	4	1	1	1	3	1
ETHYL FORMATE	23	2	4	4	4	0	0	1	0	0	1	0	1
ETHYL FORMIC ESTER	23	3	4	4	4	4	0	4	0	0	1	0	0
ETHYL HEXANOL	23	1	1	1	4	3	0	1	0	0	1	4	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
ETHYL HEXYL ACETATE	23	1	0	0	4	0	0	0	0	0	4	0	0
ETHYL HEXYL ACRYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL HEXYL ALOCOHOL	23	1	2	0	4	0	0	1	0	0	1	0	0
ETHYL IODIDE	23	0	0	0	4	0	0	0	0	0	2	0	0
ETHYL ISOVALERATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL LACTATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL MERCAPTAN	23	3	4	4	1	3	0	2	0	0	1	1	1
ETHYL MORPHOLINE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL MORPHOLINESTANNOUS OCTOTATE (50/50 MIXTURE)	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL NITRITE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL OXALATE	23	1	4	4	1	4	0	1	0	0	1	1	1
ETHYL PENTACHLOROBENZENE	23	4	4	4	4	4	0	1	0	0	1	4	1
ETHYL PYRIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL SILICATE	23	1	1	1	4	0	0	1	0	0	1	0	1
ETHYL STEARATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL SULFATE	23	1	4	0	0	0	0	2	0	0	1	0	0
ETHYL SULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL SULFURIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL TERT-BUTYL ETHER (ETBE)	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYL VALERATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE	23	4	1	1	1	4	0	1	1	1	1	1	1
ETHYLENE CHLORIDE	23	3	4	4	4	4	0	2	0	0	1	4	1
ETHYLENE CHLOROHYDRIN	23	2	4	4	4	3	1	1	0	0	1	4	1
ETHYLENE CYANOHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE DIAMINE	23	1	1	1	4	1	0	4	0	0	1	4	1
ETHYLENE DIBROMIDE	23	4	4	4	4	4	0	1	0	0	1	4	1
ETHYLENE DICHLORIDE	23	3	4	0	4	4	2	1	0	0	1	4	1
ETHYLENE GLYCOL	23	1	1	1	4	1	0	1	0	0	1	4	1
ETHYLENE GLYCOL BUTYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE GLYCOL BUTYL ETHER ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE GLYCOL ETHYL ETHER ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE GLYCOL/DISTILLED WATER (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE HYDROCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE IMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
ETHYLENE OXIDE	23	3	4	4	4	4	0	4	0	0	1	4	1
ETHYLENE TRICHLORIDE	23	3	4	4	4	4	0	1	0	0	1	4	1
ETHYLIDENE CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
EXXON FN-1973 ATF	23	0	0	0	0	0	0	0	0	0	1	0	1
EXXON FN-1975 ATF	23	0	0	0	0	0	0	0	0	0	1	0	1
EXXON WSX-8762B AFT	23	0	0	0	0	0	0	0	0	0	1	0	1
F-60 CHLORINATED SILICONE OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
F-61 CHLORINATED SILICONE OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
FAM-REFERENCE FUEL T1 (DIN 51604)	23	4	4	4	4	4	0	1	1	1	1	4	0
FAM-REFERENCE FUEL T2 (DIN 51604)	23	4	4	4	4	4	0	3	1	1	1	4	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
FAM-REFERENCE FUEL T3 (DIN 51604)	23	4	4	4	4	4	0	3	1	1	1	4	0
FATTY ACIDS	23	3	2	2	0	3	0	1	0	0	1	0	1
FEEON 31	23	0	0	0	0	0	0	0	0	0	1	0	1
FERBRIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
FERRIC ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERRIC AMMONIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERRIC CHLORIDE (AQ)	23	1	1	1	3	3	0	1	3	3	1	0	0
FERRIC FERROCYANIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERRIC HYDROXIDE	23	1	0	0	4	0	0	0	0	0	4	0	1
FERRIC NITRATE	23	1	1	1	3	3	0	1	0	0	1	1	1
FERRIC SULFATE (AQ)	23	1	1	1	3	3	0	1	0	3	1	1	1
FERROUS AMMONIUM CITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERROUS AMMONIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERROUS CARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERROUS CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERROUS IODIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERROUS SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
FERROUS TARTRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
FISH OIL	23	4	1	1	1	1	0	1	1	1	1	1	1
FLUORINATED CYCLIC ETHERS	23	1	0	0	0	0	0	0	0	0	1	0	1
FLUORINE	23	2	4	2	4	4	0	2	4	4	2	0	1
FLUORINE, LIQUID	23	4	4	4	4	4	0	2	4	4	2	4	1
FLUOROBENZENE	23	4	4	4	4	4	0	4	0	0	3	4	1
FLUOROBORIC ACID	23	1	1	1	1	0	0	0	0	0	2	0	1
FLUOROCARBON OILS	23	1	0	0	0	0	0	0	0	0	1	0	1
FLUOROHYDROGEN	23	4	4	4	4	0	0	2	0	0	1	0	0
FLUOROLUBE	23	1	1	1	0	1	0	2	0	0	1	0	1
FLUOROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
FLUOROPHOSPHORIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
FLUOROPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
FLUOROSILICIC ACID	23	2	1	1	0	4	0	1	0	0	1	0	1
FLUOROSILICIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
FLUOROSULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
FLUOROTHANE (ETHYL FLUORIDE)	23	0	0	0	0	0	0	0	0	0	1	0	1
FORMALDEHYDE	23	2	3	3	4	2	1	4	0	0	1	4	1
FORMAMIDE	23	1	0	0	2	0	0	0	0	0	3	0	1
FORMIC ACID		2	3	3	4	2	2	3	0	0	1	3	1
FR FLUID 20 (HYDRAULIC FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 11 (TRICHLOROFLUOROMETHANE)	23	4	2	2	4	0	0	2	0	0	4	0	1
FREON 11/SUNISO 3G (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 112	23	4	2	2	2	4	0	2	0	0	1	0	1
FREON 113 (TRICHLOROTRIFLUOROETHANE)	23	4	1	1	2	0	0	2	0	0	1	0	1
FREON 114 (CFC) (DICHLOROTETRAFLUOROETHANE)	23	4	1	1	1	0	0	1	0	0	1	0	1
FREON 114B2 (DIBROMOTETRAFLUOROETHANE)	23	4	2	2	4	0	0	2	0	0	1	0	1
FREON 115 (CHLOROPENTAFLUOROETHANE)	23	1	1	1	4	0	0	2	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
FREON 116 (FC) (HEXAFLUOROETHANE)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 12 (DICHLORODILUOROMETHANE)	23	2	2	1	1	0	0	2	0	0	1	0	1
FREON 12/ASTM NO.2 OIL (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 12/SUNSISSO 4G (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 123 (HCFC)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 124 (HCFC) (CHLOROTETRAFLUOROETHANE)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 125 (PENTAFLUOROETHANE)	23	0	0	0	0	0	0	0	0	0	0	0	0
FREON 13 (CHLOROTRIFLUOROMETHANE)	23	1	1	1	3	0	0	1	0	0	1	0	1
FREON 134A (HFC) (TETRAFLUOROETHANE)	23	1	1	1	4	0	0	4	0	0	1	0	1
FREON 13B1 (BROMOTRIFLUOROMETHANE)	23	1	1	1	1	0	0	2	0	0	1	0	1
FREON 14 (TETRAFLUOROMETHANE)	23	1	0	0	1	0	0	0	0	0	1	0	1
FREON 141B (HCFC)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 142B (HCFC) (DIFLUOROCHLOROETHANE)	23	1	1	2	0	0	0	4	0	0	1	0	1
FREON 143A (1,1,1-TRIFLUOROETHANE)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 152A (HFC) (DIFLUOROETHANE)	23	1	1	0	1	0	0	4	0	0	4	0	1
FREON 152B	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 21 (HCFC) (DICHLOROFLUOROMETHANE)	23	4	4	4	4	0	0	4	0	0	4	0	1
FREON 218	23	1	1	0	0	0	0	2	0	0	1	0	1
FREON 22 (HCFC) (CHLOROFLUOROMETHANE)	23	1	4	4	4	0	0	4	0	0	4	0	1
FREON 23 (HCFC) (FLUOROFORM)	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON 31	23	1	4	0	2	0	0	4	0	0	4	0	1
FREON 32	23	1	1	1	0	0	0	4	0	0	1	0	1
FREON 502	23	3	2	0	1	0	0	0	0	0	1	0	1
FREON BF	23	4	2	2	0	4	0	2	0	0	1	0	1
FREON C316	23	1	1	0	1	0	0	1	0	0	1	0	1
FREON C318 (CFC)(OCTAFLUOROTETRAETHYLENE)	23	1	1	1	0	0	0	1	0	0	1	0	1
FREON MCA	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON MF	23	4	1	2	3	4	0	2	0	0	1	3	1
FREON MF	23	4	1	2	3	4	0	2	0	0	1	3	1
FREON PCA	23	4	1	1	1	0	0	2	0	0	0	0	1
FREON SMT	23	0	0	0	0	0	0	0	0	0	1	0	1
FREON TA	23	2	1	0	1	3	0	4	0	0	1	1	1
FREON TC	23	2	1	0	1	4	0	2	0	0	1	1	1
FREON TF	23	4	1	1	1	4	4	2	0	0	1	1	1
FREON TMC	23	3	2	0	2	3	0	2	0	0	1	2	1
FREON T-P 35	23	1	1	1	1	0	0	1	0	0	1	0	1
FREON T-WD 602	23	2	2	0	3	0	0	1	0	0	1	0	1
FRUIT-JUICE	23	1	1	1	3	1	0	1	1	1	1	1	0
FRYQUEL 220 (MIL-G-23652 TYPE I)	23	0	0	0	0	0	0	0	0	0	1	0	1
FRYQUEL 220 (MIL-G-23652 TYPE II)	23	0	0	0	0	0	0	0	0	0	1	0	1
FRYQUEL A60	23	0	0	0	0	0	0	0	0	0	1	0	1
FRYQUEL EHC	23	0	0	0	0	0	0	0	0	0	1	0	1
FS-1280 FLUOROSILICONE	23	0	0	0	0	0	0	0	0	0	1	0	1
FS-1281 FLUOROSILICONE	23	0	0	0	0	0	0	0	0	0	1	0	1
FUEL OIL	23	4	1	1	2	4	0	1	0	0	1	2	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
FUEL OIL, HEAVY	40	4	3	3	3	3	0	1	1	1	1	1	0
FUEL OIL, LIGHT	40	4	1	1	3	3	0	1	1	1	1	1	0
FUEL TYP II (Mil-S-3136)		1	4	2	4	0	0	0	0	0	1	0	0
FUMARIC ACID	23	2	1	1	0	2	0	1	0	0	1	0	1
FURALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
FURAN	23	4	4	4	4	4	0	4	0	0	1	0	0
FURFUR ALCOHOL	n.a.	1	4	4	4	4	0	4	0	0	1	4	0
FURFURAL	23	2	4	4	3	4	2	4	0	0	1	3	1
FURFURAN	23	0	0	0	0	0	0	0	0	0	1	0	1
FURFUROL (A-FURFURYLALDEHYDE)	23	1	4	4	4	4	0	4	1	2	1	4	0
FURFURYL ALCOHOL	23	2	4	4	4	0	0	4	0	0	1	0	1
FURNACE GAS		4	4	4	4	0	0	1	0	0	1	0	0
FUROIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
FYRQUEL (CELLULUBE)	23	1	4	4	4	1	0	1	0	0	1	4	1
FYRQUEL® 90, 100, 150, 220, 300, 500, 550	23	0	0	0	0	0	0	0	0	0	1	0	1
GALLIC ACID	23	2	2	2	4	0	0	1	0	0	1	4	1
GALVANISING SOLVENTS(CHROM)	23	1	4	4	4	0	0	1	0	0	1	0	0
GAMMA-RAYS	20	3	3	3	1	3	0	4	4	3	4	1	0
GAS OIL	23	4	1	1	2	4	0	1	1	1	1	2	0
GASOLINE	23	4	2	1	3	4	2	1	0	0	1	2	1
GASOLINE (20% ETHANOL)	23	4	3	3	4	4	0	1	0	0	1	4	0
GASOLINE (20% METHANOL)	23	4	4	4	4	4	0	3	0	0	1	4	0
GASOLINE ANTIOXIDANT NO.22	23	0	0	0	0	0	0	0	0	0	1	0	1
GASOLINE HIGH-OCTANE	23	4	3	3	3	4	0	1	1	1	1	3	0
GASOLINE M-15 (15% METHANOL)	23	4	4	4	4	4	0	3	1	1	1	4	0
GASOLINE PREMIUM (LEADED)	23	0	0	0	0	0	0	0	0	0	1	0	1
GASOLINE PREMIUM (UNLEADED)	23	0	0	0	0	0	0	0	0	0	1	0	1
GASOLINE, 92 OCTANE	23	4	1	1	3	4	0	1	1	1	1	3	0
GASOLINE, 98 OCTANE	23	4	3	4	3	4	0	1	1	1	1	3	0
GASOLINE, REFINED	23	4	1	1	1	4	0	1	1	1	1	1	0
GEAR LUBES SAE 80 / SAE 90	80	4	1	1	0	3	0	1	0	0	1	0	0
GEAR LUBES, HYPOID LUBES, ATF	80	4	3	1	0	4	0	1	4	1	1	0	0
GEAR LUBRICANT (GL-4A)	23	0	0	0	0	0	0	0	0	0	1	0	1
GEAR LUBRICANT (GL-4B)	23	0	0	0	0	0	0	0	0	0	1	0	1
GEAR LUBRICANT (HD-90)	23	0	0	0	0	0	0	0	0	0	1	0	1
GEAR LUBRICANT (LEAD SOAP ACTIVE)	23	0	0	0	0	0	0	0	0	0	1	0	1
GEAR LUBRICANT (SCL)	23	0	0	0	0	0	0	0	0	0	1	0	1
GEAR LUBRICANT (SULFUR MIL-L-2105)	23	0	0	0	0	0	0	0	0	0	1	0	1
GELATIN	23	1	1	1	4	1	0	1	1	1	1	4	1
GENERATOR GAS	23	4	1	1	1	3	0	1	0	0	1	0	1
GIRLING CRIMSON (BRAKE FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
GLAUBERS SALT	23	2	4	4	0	0	0	1	0	0	1	0	1
GLUCONIC ACID	23	1	0	0	4	0	0	0	0	0	1	0	1
GLUCOSE	23	1	1	1	4	1	0	1	0	0	1	4	1
GLUE	23	1	1	1	1	1	0	1	0	0	1	1	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
GLUTAMIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCERIN	23	1	1	1	4	1	1	1	1	1	1	1	1
GLYCEROL	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCEROL DICHLORHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCEROL MONOCHLORHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCEROL TRIACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCEROPHOSPHORIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCERYL PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCIDOL	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCINE	23	1	0	0	2	0	0	0	0	0	1	0	0
GLYCOL ETHYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCOL MONOETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCOLIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
GLYCOLS	23	1	1	1	4	1	0	1	0	0	1	4	1
GLYCOXYLIC ACID	23	1	0	1	2	0	0	0	0	0	1	0	1
GLYSANTINE (ANTIFREEZE)	140	1	1	1	4	1	0	1	0	0	1	4	0
GLYSANTINE /WATER (40: 60 VOL%)	100	1	3	3	4	0	0	1	1	2	1	0	0
GREASE (MACHINE OIL NO.120)	23	0	0	0	0	0	0	0	0	0	1	0	1
GREASE (MAGNET)	23	0	0	0	0	0	0	0	0	0	1	0	1
GREASE (SHALLOW)	23	0	0	0	0	0	0	0	0	0	1	0	1
GREASE, ANIMAL BASE	50	3	1	1	1	1	0	1	1	1	1	1	0
GREASE, PETROLEUM BASE	50	4	1	1	1	4	0	1	1	1	1	1	0
GREASE, VEGETABLEBASE	50	4	1	1	1	1	0	1	1	1	1	1	0
GREEN SULFATE LIQUOR	23	1	2	2	1	1	0	1	0	0	1	1	1
GULF ENDURANCE OILS	23	0	0	0	0	0	0	0	0	0	1	0	1
H-17(HUNGARY)	60	4	1	1	4	4	0	1	1	3	1	1	0
HALON 1211 (FIRE-EXTINGUISHING MEDIUM)	23	4	4	4	1	4	0	3	0	0	1	1	0
HALON 1301	23	1	1	1	1	4	0	1	0	0	1	1	0
HALOTHANE (BROMOCLOROTRIFLUOROETHANE)	23	4	4	4	4	0	0	1	0	0	1	0	1
HALOWAX OIL	23	4	4	4	4	4	0	1	0	0	1	0	1
HANOVER (MIL-H-83282)	23	0	0	0	0	0	0	0	0	0	1	0	1
HEAVY WATER	23	1	1	0	4	0	0	1	0	0	1	0	1
HEF-2 (TRIALKYL PENTABORANE)	23	4	2	2	3	0	0	1	0	0	1	0	1
HEF-3	23	0	0	0	0	0	0	0	0	0	1	0	1
HELIUM	23	1	1	1	1	0	0	1	0	0	1	0	1
HEPTACHLOR	23	0	0	0	0	0	0	0	0	0	1	0	1
HEPTACHLOROBUTENE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEPTADECANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
HEPTANAL	23	1	0	0	4	0	0	0	0	0	2	0	1
HEPTANE	23	4	1	1	2	4	0	1	1	1	1	0	1
HEPTANOIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
HEPTANONE	23	3	4	4	4	4	0	4	0	0	1	4	0
HEPTYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
HERBAL OIL AND FAT	23	3	1	1	2	0	0	1	0	0	1	0	0
HERCOFLEX 600	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
HESSOL BIOL HE 46	80	4	4	4	3	4	0	1	1	1	1	1	0
HESSOL BIOL HR 37	80	4	4	4	3	4	0	1	1	1	1	1	0
HEXACHLOROACETONE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXACHLOROBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXACHLOROBUTADIENE	23	1	4	0	4	0	0	0	0	0	1	0	1
HEXACHLOROBUTENE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXACHLOROCYCLOHEXANE	23	4	4	4	3	4	0	1	1	4	1	0	0
HEXACHLOROETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXADECANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAETHYL TETRAPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAFLUOROETHANE (F-116)	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAFLUOROPROPYLENE EPOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAFLUROXYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAMETHYLDISILIZANE (HMDS)	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAMETHYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAMETHYLENE DIAMMONIUM ADIPATE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAMETHYLENEDIAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXAMETHYLENETETRAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXANE	23	4	1	1	2	4	0	1	1	1	1	2	1
HEXANONE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXONE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXONE (METHYL ISOBUTYL KETONE)	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXYL ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXYL ALCOHOL	23	3	3	3	4	2	0	1	0	1	1	4	1
HEXYLENE GLYCOL	23	0	0	0	0	0	0	0	0	0	1	0	1
HEXYLRESORCINOL	23	0	0	0	0	0	0	0	0	0	1	0	1
HIGH VISCOSITY LUBRICANT H2	23	0	0	0	0	0	0	0	0	0	1	0	1
HIGH VISCOSITY LUBRICANT U4	23	0	0	0	0	0	0	0	0	0	1	0	1
HOUGHTON VITAL 29 FM (HYDRAULIC FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
HOUGHTO-SAFE 1010, 1055	50	1	4	4	4	4	0	1	0	0	1	4	0
HOUGHTO-SAFE 271, 620	50	1	1	1	4	3	0	3	1	3	1	3	0
HOUGHTO-SAFE 5040	50	4	1	1	4	4	0	1	1	3	1	2	0
HYDRA - VIS (HOUGHTON VAUGHAN)	70	4	4	4	4	4	0	4	1	3	1	4	0
HYDRAULIC FLUID HFA (OIL IN WATER)	50	4	1	1	4	3	0	1	1	3	1	1	0
HYDRAULIC FLUID HFB (WATER IN OIL)	50	4	1	1	4	0	0	1	1	3	1	1	0
HYDRAULIC FLUID HFC (POL YALKYLENE-GLYCOL)	140	1	1	1	4	0	0	3	1	3	1	3	0
HYDRAULIC FLUID HFD-R (PHOSPHATE ESTER)	100	1	4	4	4	4	0	1	0	0	1	4	0
HYDRAULIC FLUID HFD-S (CHLOR.HYDROCARB.)	100	4	4	4	4	0	0	1	0	0	1	4	0
HYDRAULIC FLUID HFD-U (SYNTH. ESTER)	80	4	4	2	4	4	0	1	1	1	1	1	0
HYDRAULIC OIL (PETROLEUM BASE)	23	4	1	1	1	3	0	1	1	1	1	1	1
HYDRAULIC OILS (SYNTHETIC BASE)	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDRAZINE	23	1	2	4	4	3	0	4	1	0	1	4	1
HYDRAZINE DIHYDROCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDRIODIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
HYDROABIETYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROBROMIC ACID	23	1	4	4	4	4	0	1	0	0	1	4	1
HYDROBROMIC ACID 40%	23	1	4	4	4	4	0	1	4	4	1	4	1
HYDROCARBONS	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROCHLORIC ACID (COLD) 37%	n.a.	2	3	3	4	3	1	1	0	0	1	4	1
HYDROCHLORIC ACID (CONC.)	23	4	4	3	4	0	0	4	0	0	1	0	1
HYDROCHLORIC ACID (HOT) 37%	n.a.	3	4	3	4	4	2	2	0	0	1	4	1
HYDROCHLORIC ACID 10%	40	1	3	3	4	3	0	1	4	4	1	3	0
HYDROCHLORIC ACID FUMING	23	3	4	4	4	4	0	4	4	4	1	4	0
HYDROCHLORIC ACID/CHLORINE GAS	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROCYANIC ACID	23	1	2	2	4	3	0	1	0	0	1	0	1
HYDROFLUORIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROFLUORIC ACID (CONC.) COLD	n.a.	3	4	4	3	4	1	1	0	0	1	3	1
HYDROFLUORIC ACID (CONC.) HOT	n.a.	4	4	4	4	4	0	4	0	0	1	4	1
HYDROFLUORIC ACID 48%	23	1	4	4	4	4	0	1	4	4	1	4	0
HYDROFLUORIC ACID 75%	23	1	4	4	4	4	0	3	4	4	1	4	0
HYDROFLUORIC ACID ANHYDROUS	23	3	4	0	4	4	0	4	0	0	1	4	1
HYDROFLUORSILICIC ACID (FLUORSILICIC ACID)	23	2	1	1	0	4	0	1	0	0	1	0	1
HYDROGEN	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROGEN BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROGEN CHLORIDE	23	1	4	4	4	4	0	1	4	4	1	4	1
HYDROGEN CYANIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROGEN FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROGEN FLUORIDE, DRY	23	3	4	4	4	4	0	1	0	0	1	4	0
HYDROGEN GAS	23	1	1	1	1	4	0	1	1	1	1	1	1
HYDROGEN IODIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROGEN PEROXIDE 30%	23	1	4	4	4	3	0	1	4	4	1	1	0
HYDROGEN PEROXIDE 90%	23	2	4	2	4	2	0	2	0	0	1	0	1
HYDROGEN SELENIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDROGEN SULFIDE	23	1	3	3	3	4	0	4	1	2	1	0	1
HYDROGEN SULFIDE (WET) COLD	23	1	4	1	0	3	0	4	0	0	1	0	1
HYDROGEN SULFIDE (WET) HOT	23	1	4	4	0	3	0	4	0	0	1	0	1
HYDROLUBE	23	1	1	0	4	0	0	1	0	0	1	0	1
HYDROLUBRIC 120B	60	1	1	1	4	1	0	1	1	3	1	1	1
HYDROQUINONE	23	3	4	4	4	4	0	2	0	4	1	4	1
HYDROXYACETIC ACID	23	1	0	1	2	0	0	0	0	0	1	0	1
HYDROXYL-AMINE SULFATE, AQ. SOL.	23	1	1	1	4	1	0	1	1	3	1	0	0
HYDYNE	23	0	0	0	0	0	0	0	0	0	1	0	1
HYDYNE (UNS-DIMETHYL HYDRAZINE/DIETHYLENE TRIAMINE)	23	0	0	0	0	0	0	0	0	0	1	0	1
HYJET S, W, III	23	0	0	0	0	0	0	0	0	0	1	0	1
HYPOCHLOROUS ACID	23	2	4	4	4	4	0	1	0	0	1	4	1
HY-TRANS-PLUS MS 1207 (CASE)	80	4	3	1	1	4	0	1	0	0	1	1	0
INDOLE	23	0	0	0	0	0	0	0	0	0	1	0	1
INDUSTRON	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
INSULIN	23	0	0	0	0	0	0	0	0	0	1	0	1
IODIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
IODINE	23	2	2	1	4	0	0	1	0	0	1	0	1
IODINE PENTAFLUORIDE	23	4	4	4	4	4	0	4	0	0	1	4	1
IODOBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
IDOETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
ODOFORM	23	4	0	0	0	0	0	3	4	4	1	4	1
ODOMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
ODOPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
I-PROPYL ACETATE	23	2	4	0	4	4	0	4	0	0	1	4	1
ISO DODECANE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOAMYL ACETATE	23	2	4	0	0	0	0	4	0	0	1	0	1
ISOAMYL ALCOHOL	23	1	1	0	0	0	0	1	0	0	1	0	1
ISOAMYL BUTYRATE	23	1	0	0	4	0	0	0	0	0	4	0	1
ISOAMYL CHLORIDE	23	1	0	0	4	0	0	0	0	0	2	0	0
ISOAMYL VALERATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBOREOL	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTANE	23	1	0	0	4	0	0	0	0	0	1	0	1
ISOBUTENE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYL ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYL ACRYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYL ALCOHOL	23	1	2	2	4	1	0	1	0	0	1	4	1
ISOBUTYL ALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYL AMINE	23	1	0	0	2	0	0	0	0	0	4	0	0
ISOBUTYL CHLORIDE	23	2	3	4	0	0	0	1	0	0	1	0	1
ISOBUTYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYL METHYL KETONE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYL N-BUTYRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYL PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOBUTYRIC ACID	23	1	3	2	0	0	0	4	0	0	1	0	0
ISOCYANATES	23	0	0	0	0	0	0	0	0	0	1	0	1
ISODECANE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISODECANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
ISODODECANE	23	4	1	1	0	0	0	1	0	0	1	0	0
ISOEUGENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOCTANE	23	4	1	1	2	4	2	1	0	0	1	2	1
ISOPENTANE	23	1	0	0	4	0	0	0	0	0	1	0	1
ISOPHORONE	23	3	4	4	3	4	2	4	0	0	1	3	1
ISOPROPANOL	23	1	3	3	4	1	0	1	1	1	1	4	0
ISOPROPYL ACETATE	23	2	4	4	4	4	0	4	0	0	1	4	1
ISOPROPYL ACETONE	23	0	0	0	0	0	0	0	0	0	1	0	1
ISOPROPYL ALCOHOL	23	1	2	2	3	1	0	1	0	0	1	3	1
ISOPROPYL AMINE	23	1	0	0	2	0	0	0	0	0	4	0	0
ISOPROPYL BENZENE	23	4	4	4	4	0	0	1	0	0	1	0	0

0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
ISOPROPYL CHLORIDE	23	4	4	4	4	4	0	1	0	0	1	4	1
ISOPROPYL ETHER	23	4	2	2	2	4	4	4	0	0	1	2	1
ISOVALERIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
JAM	23	1	1	1	3	1	0	1	1	1	1	1	0
JET FUEL - JET A1	23	4	1	1	4	4	0	1	0	0	1	2	1
JP-3 (MIL-T-5624)	23	0	0	0	0	0	0	0	0	0	1	0	1
JP-4 (MIL-T-5624)	23	0	0	0	0	0	0	0	0	0	1	0	1
JP-5 (MIL-T-5624)	23	0	0	0	0	0	0	0	0	0	1	0	1
JP-6 (MIL-F-25656)	23	0	0	0	0	0	0	0	0	0	1	0	1
JP-7	23	0	0	0	0	0	0	0	0	0	1	0	1
JP-8 (MIL-T-83133)	23	0	0	0	0	0	0	0	0	0	1	0	1
JP-9 (MIL-F-81912)	23	0	0	0	0	0	0	0	0	0	1	0	1
JPX- (MIL-F-25604)	23	0	0	0	0	0	0	0	0	0	1	0	1
KEARSLEY THINNERS	23	0	0	0	0	0	0	0	0	0	1	0	1
KEL-F LIQUIDS	23	1	1	0	0	0	0	2	0	0	1	0	0
KEROSENE	23	4	1	1	1	4	1	2	0	0	1	1	1
KETCHUP	50	1	1	1	3	1	0	1	0	0	1	1	0
KETONES	23	0	0	0	0	0	0	0	0	0	1	0	1
KLOBER SYNTHESO D 220 - EP (GLYCOL)	80	0	3	3	0	0	0	0	0	0	0	0	0
KLOBER SYNTHESO PROBA 270 (L1THIUM-GREJ)	50	1	1	1	1	0	0	1	0	0	1	1	0
KRYPTON	23	0	0	0	0	0	0	0	0	0	1	0	1
KRYTOX®	23	0	0	0	0	0	0	0	0	0	1	0	1
LACQUER SOLVENTS	23	4	4	4	4	4	4	4	0	0	1	4	1
LACQUERS	23	4	4	4	4	4	0	4	0	0	1	4	1
LACTAMS (AMINO ACIDS)	23	2	4	4	0	0	0	4	0	0	1	0	0
LACTIC ACID (COLD)	23	1	1	1	1	1	0	1	0	0	1	0	1
LACTIC ACID (HOT)	23	4	4	4	4	2	0	1	0	0	1	0	1
LARD (ANIMAL FAT)	23	2	1	1	1	2	0	1	0	0	1	1	1
LAUGHING GAS	23	1	1	1	1	1	0	1	1	1	1	1	0
LAURIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
LAURYL ALCOHOL	23	1	1	1	4	0	0	3	0	0	2	4	0
LAVENDER OIL	23	4	2	2	4	4	0	1	1	1	1	4	1
LEAD (MOLTEN)	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD ACETATE (AQ)	23	1	2	2	4	4	0	4	0	0	1	4	1
LEAD ARSENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD AZIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD CARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD CHLORIDE	23	1	0	0	0	0	0	0	0	0	0	0	0
LEAD CHROMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD DIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD LINOLEATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD NAPHTHENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LEAD NITRATE	23	1	1	1	4	2	0	1	0	0	1	0	1
LEAD OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
LEAD SULFAMATE	23	1	4	1	2	2	0	1	0	0	1	0	1
LIGHT LUBRICANTS		4	1	1	1	0	0	1	0	0	1	0	0
LIGROIN (BENZINE) (NITROBENZINE) (PET ETHER)	23	4	1	1	2	4	0	1	0	0	1	2	1
LIME BLEACH	23	1	1	1	4	2	0	1	0	0	1	0	1
LIME SULFUR	23	1	4	1	0	1	0	1	0	0	1	0	1
LINDOL (HYDRAULIC FLUID)	23	1	4	4	4	3	0	2	0	0	1	4	1
LINOLEIC ACID	23	4	2	2	3	2	0	2	0	0	1	0	1
LINSEED OIL	23	4	1	1	2	3	0	1	0	0	1	2	1
LIQUEUR (MAX. 30% ALCOHOL)	23	1	1	1	4	1	0	1	1	3	1	0	0
LIQUID OXYGEN	23	4	4	4	4	0	0	4	0	0	1	0	1
LIQUID PETROLEUM GAS	23	1	3	3	4	0	0	4	0	0	1	0	0
LIQUIMOLY	23	4	1	1	2	0	0	1	0	0	1	0	0
LITHIUM BROMIDE AQ. SOL.	23	1	1	0	4	1	0	1	1	3	1	0	1
LITHIUM CARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LITHIUM CHLORIDE	23	1	1	0	1	0	0	1	0	0	1	0	1
LITHIUM CITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LITHIUM HYDROXIDE	23	1	0	0	0	0	0	0	0	0	1	0	1
LITHIUM HYPOCHLORITE	23	0	0	0	0	0	0	0	0	0	1	0	1
LITHIUM NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LITHIUM NITRITE	23	0	0	0	0	0	0	0	0	0	1	0	1
LITHIUM PERCHLORATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LITHIUM SALICYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
LITHOPONE	23	1	0	0	0	0	0	0	0	0	1	0	1
LUBRICATING OILS PETROLEUM BASE	23	4	1	4	2	4	0	1	0	0	1	2	1
LUBRICATING OILS, DIESTER	23	4	2	0	4	0	0	1	0	0	1	0	1
LYE	23	1	2	2	4	2	0	2	0	0	1	4	1
MACK TRUCK ENGINE COOLANT	23	0	0	0	0	0	0	0	0	0	1	0	1
MAGNESIUM ACETATE	23	1	0	0	4	0	0	0	0	0	4	0	0
MAGNESIUM CHLORIDE (AQ)	23	1	1	1	3	1	1	1	1	3	1	1	1
MAGNESIUM HYDROXIDE (AQ)	23	1	2	2	4	0	0	1	1	3	1	4	1
MAGNESIUM SALTS	23	1	1	1	1	0	0	1	0	0	1	0	0
MAGNESIUM SULFATE	23	1	1	0	4	1	0	1	0	0	1	0	1
MAGNESIUM SULFITE	23	0	0	0	0	0	0	0	0	0	1	0	1
MAGNESIUM TRISILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
MAIZE OIL	23	4	1	1	1	1	0	1	1	1	1	1	0
MALATHION	23	1	0	2	4	0	0	0	0	0	1	0	1
MALEIC ACID	23	2	4	4	4	4	0	1	0	0	1	3	1
MALEIC ANHYDRIDE	23	2	4	4	0	0	0	4	0	0	1	0	1
MALIC ACID	23	4	1	1	4	3	0	1	1	3	1	0	1
MANDELIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
MANGANESE ACETATE	23	1	0	0	0	0	0	0	0	0	1	0	1
MANGANESE CARBONATE	23	1	0	0	0	0	0	0	0	0	1	0	1
MANGANESE CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
MANGANESE DIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
MANGANESE GLUCONATE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
MANGANESE HYPOPHOSPHITE	23	0	0	0	0	0	0	0	0	0	1	0	1
MANGANESE LINOLEATE	23	0	0	0	0	0	0	0	0	0	1	0	1
MANGANESE NAPHTHENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
MANGANESE SALTS	23	0	0	0	0	0	0	0	0	0	1	0	1
MANGANESE SULFATE	23	1	0	0	3	0	0	0	0	0	1	0	1
MANGANESE SULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
MANNITOL	23	0	0	0	0	0	0	0	0	0	1	0	1
MARGARINE	40	4	1	1	4	1	0	1	1	1	1	0	0
MARSH GAS	23	4	1	1	3	4	0	1	1	1	1	0	0
MAYONNAISE	50	4	1	1	4	1	0	3	1	1	1	0	0
MBT	23	0	0	0	0	0	0	0	0	0	1	0	1
MDI	23	0	0	0	0	0	0	0	0	0	1	0	1
MEA (ETHANOLAMINE)	23	0	0	0	0	0	0	0	0	0	1	0	1
MEK/TOLUENE (50%/50%)	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCAPTAN	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCAPTOBENZOTHAZOLE	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCURIC ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCURIC CHLORIDE	23	1	1	1	0	0	0	1	0	0	1	0	0
MERCURIC CYANIDE	23	1	2	0	0	0	0	1	0	0	1	0	0
MERCURIC IODIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCURIC NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCURIC SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCURIC SULFITE	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCUROUS NITRATE	23	1	2	0	0	0	0	1	0	0	1	0	1
MERCURY	23	1	1	1	1	0	0	1	0	0	1	1	1
MERCURY CHLORIDE (AQ)	23	1	1	1	4	1	0	1	1	4	1	0	1
MERCURY FULMINATE	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCURY SALTS	23	0	0	0	0	0	0	0	0	0	1	0	1
MERCURY VAPOR	23	0	0	0	0	0	0	0	0	0	1	0	1
MESITYL OXIDE	23	2	4	4	4	4	4	4	1	2	1	4	1
METACRESOL	23	0	0	0	0	0	0	0	0	0	1	0	1
METALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
METANITROANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
METATOLUIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHACRYLIC ACID	23	2	4	4	0	0	0	3	0	0	1	0	1
METHACRYLIC METHYLESTER	23	1	4	0	4	0	0	0	0	0	4	0	0
METHANE	23	4	1	1	3	4	0	1	1	1	1	3	1
METHANETHIOL	23	0	0	0	0	0	0	0	0	0	1	0	1
METHANOL	23	1	3	3	4	1	0	4	1	1	1	4	0
METHOXYCHLOR	23	0	0	0	0	0	0	0	0	0	1	0	1
METHOXYETHANOL (DGMMA)	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL ABIETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL ACETATE	23	2	4	4	4	4	0	4	0	0	1	4	1
METHYL ACETOACETATE	23	2	4	4	4	0	0	4	0	0	1	0	0
METHYL ACETOPHENONE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
METHYL ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL ACRYLATE	23	2	4	4	4	4	0	4	0	0	1	4	1
METHYL ALCOHOL	23	1	1	1	4	1	1	4	0	0	1	4	1
METHYL AMINE	23	1	3	3	4	4	0	4	1	1	1	4	1
METHYL AMYL ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL AMYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL AMYLKETONE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL ANTHRANILATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL BENZOATE	23	4	4	4	4	0	0	1	0	0	1	0	1
METHYL BENZYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL BROMIDE	23	4	4	4	4	4	0	1	1	1	1	4	1
METHYL BUTYL KETONE (PROPYL ACETONE)	23	1	4	4	4	3	0	4	0	0	1	4	1
METHYL BUTYRATE	23	1	0	0	0	0	0	0	0	0	0	0	0
METHYL CARBONATE	23	4	4	4	4	0	0	1	0	0	1	0	1
METHYL CELLOSOLVE	23	2	3	3	4	4	1	4	0	0	1	4	1
METHYL CELLULOSE	23	2	2	2	2	0	0	4	0	0	1	0	1
METHYL CHLORIDE	23	3	4	4	4	4	0	2	1	1	1	4	1
METHYL CHLOROACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL CHLOROFORM	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL CHLOROFORMATE	23	4	4	4	4	0	0	1	0	0	1	0	1
METHYL CHLOROSILANES	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL CYANIDE	23	1	2	2	0	0	0	1	0	0	1	0	1
METHYL CYCLOHEXANONE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL CYCLOPENTANE	23	4	4	4	4	4	0	1	0	0	1	4	1
METHYL DICHLORIDE	23	1	4	2	4	0	0	4	0	0	1	0	1
METHYL ETHER (DIMETHYL ETHER) (MONOMETHYL ETHER)	23	4	1	1	0	1	0	4	0	0	1	0	1
METHYL ETHYL KETONE	23	2	4	4	4	4	4	4	0	0	1	4	1
METHYL ETHYL KETONE PEROXIDE	23	4	4	4	4	0	0	4	0	0	1	0	1
METHYL ETHYL OLEATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL FORMATE	23	3	4	4	4	3	0	4	0	0	1	4	1
METHYL GLYCEROL	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL GLYCOLACETATE		1	4	0	3	0	0	0	0	0	4	0	0
METHYL HEXYL KETONE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL IODIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
METHYL ISOAMYL KETONE (MIAK)	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL ISOBUTYL KETONE	23	3	4	4	4	4	4	4	0	0	1	4	1
METHYL ISOCYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL ISOPROPYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL ISOPROPYL KETONE	23	2	4	4	4	0	0	4	0	0	1	0	1
METHYL ISOVALERATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL LACTATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL LAURATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL MERCAPTAN	23	1	0	0	0	0	0	0	0	0	0	0	1
METHYL METHACRYLATE	23	3	4	4	4	4	0	4	0	0	1	4	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
METHYL N-AMYLKETONE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL OLEATE	23	2	4	4	4	4	0	2	0	0	1	0	1
METHYL PENTADIENE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL PHENYL SILICONE FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL PHENYLACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL PHENYLETHER		1	0	0	4	0	0	0	0	0	3	0	0
METHYL PROPYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL PROPYL KETONE	23	1	1	0	4	0	0	2	0	0	1	0	1
METHYL PYRROLIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL PYRROLIDONE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL SALICYLATE	23	2	4	0	0	0	3	2	0	0	1	0	1
METHYL SULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL SULFURIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL TERT BUTYL ETHER (MTBE)	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL VALERATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYL VINYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYLACRYLIC ACID	23	2	4	4	4	4	0	4	0	0	3	4	1
METHYLAMINE	23	1	0	0	2	0	0	0	0	0	2	0	1
METHYLAMYL ACETATE	23	1	0	0	0	0	0	0	0	0	4	0	1
METHYLCYCLOPENTANE	23	4	4	4	4	3	0	1	0	0	1	4	0
METHYLENE BLUE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYLENE BROMIDE	23	1	0	0	4	0	0	0	0	0	2	0	1
METHYLENE CHLORIDE	23	3	4	4	4	4	2	3	3	4	1	4	1
METHYLENE DICHLORIDE	23	4	4	4	4	4	0	2	3	3	1	4	0
METHYLENE DI-P-PHENYLENE ISOCYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYLENE IODIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
METHYLISOBUTYL CARBINOL	23	0	0	0	0	0	0	0	0	0	1	0	1
MIDCONTINENT ASPHALT (85-100)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-1-8660 B	23	1	1	0	1	4	0	1	0	0	1	1	1
MIL-A-8243 B	23	1	1	0	3	2	0	2	0	0	1	3	1
MIL-C-4339 C	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-C-5545 A	23	4	2	0	3	4	0	1	0	0	1	3	1
MIL-C-6529 C	23	4	2	0	3	4	0	1	0	0	1	3	1
MIL-C-8188 C	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-F-16929 A	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-F-16958 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-F-17111	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-F-19605	23	4	1	0	3	4	0	1	0	0	1	3	1
MIL-F-25172	23	4	1	0	3	4	0	1	0	0	1	3	1
MIL-F-25524 A	23	4	1	0	3	4	0	1	0	0	1	3	1
MIL-F-25558 (RJ-1)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-F-25558 B (RJ-1)	23	4	1	1	1	3	0	1	0	0	1	1	1
MIL-F-25576 C (RP-1)	23	4	1	1	1	4	0	1	0	0	1	1	1
MIL-F-25656 (JP-6)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-F-25656 B	23	4	1	0	3	4	0	1	0	0	1	3	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
MIL-F-5566	23	1	1	0	2	1	0	1	0	0	1	2	1
MIL-F-5602	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-F-7024 A	23	4	1	0	2	4	0	1	0	0	1	2	1
MIL-F-81912 (JP-9)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-F-82522 (RJ-4)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-G-10924 B	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-G-15793	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-G-18709 A	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-G-2108	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-G-23827 A	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-G-25013 D	23	1	1	0	3	4	0	1	0	0	1	3	1
MIL-G-25537 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-G-25760 A	23	4	1	0	2	4	0	1	0	0	1	2	1
MIL-G-27343	23	1	1	0	1	4	0	1	0	0	1	1	1
MIL-G-27617	23	1	4	0	0	4	0	1	0	0	1	0	1
MIL-G-4343 B	23	3	2	0	1	4	0	1	0	0	1	1	1
MIL-G-7118 A	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-G-7187	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-G-7421 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-G-7711 A	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-H-13862	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-H-13866 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-H-13910 B	23	1	2	0	3	4	0	1	0	0	1	3	1
MIL-H-13919 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-H-19457 B	23	1	4	0	4	4	0	4	0	0	1	4	1
MIL-H-22072	23	1	1	0	3	2	0	2	0	0	1	3	1
MIL-H-25598	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-H-27601 A	23	4	2	0	3	4	0	1	0	0	1	3	1
MIL-H-46001 A	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-H-46004	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-H-5559 A	23	1	1	0	3	2	0	2	0	0	1	3	1
MIL-H-5606 B (RED OIL)	23	4	1	1	1	4	0	1	0	0	1	1	1
MIL-H-6083 C	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-H-7083 A	23	1	1	0	3	2	0	2	0	0	1	3	1
MIL-H-7644	23	1	2	0	3	4	0	1	0	0	1	3	1
MIL-H-81019 B	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-H-8446 (MLO-8515)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-H-8446 B (MLO-8515)	23	4	2	0	4	4	0	1	0	0	1	4	1
MIL-I-27686 D	23	1	1	0	3	2	0	2	0	0	1	3	1
MIL-J-5161 F	23	4	1	0	3	4	0	1	0	0	1	3	1
MIL-J-5624 G JP-3, JP-4, JP-5	23	4	1	1	3	4	0	1	0	0	1	3	1
MILK	23	1	1	1	4	1	1	1	1	1	1	1	1
MIL-L-10295 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-L-10324 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-L-11734 B	23	4	1	0	3	3	0	1	0	0	1	3	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
MIL-L-14107 B	23	4	3	0	0	4	0	1	0	0	1	0	1
MIL-L-15017	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-15018 B	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-15019 C	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-15719 A	23	2	2	0	4	4	0	1	0	0	1	4	1
MIL-L-17331 D	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-17353 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-L-17672 B	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-18486 A	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-19701	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-L-2104 B	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-2105 B	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-21260	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-21568 A	23	1	1	0	0	4	0	1	0	0	1	0	1
MIL-L-22396	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-23699	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-L-23699 A	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-L-23699 LUBRICANTS	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-L-25336 B	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-L-25681 C	23	1	1	0	3	4	0	1	0	0	1	3	1
MIL-L-25968	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-L-26087 A	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-27694 A	23	1	1	0	1	4	0	1	0	0	1	1	1
MIL-L-3150 A	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-3503	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-L-3545-B	23	4	2	0	3	4	0	1	0	0	1	3	1
MIL-L-46000 A	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-L-46002	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-5020 A	23	4	1	0	2	4	0	1	0	0	1	2	1
MIL-L-6082 C	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-6085 A	23	4	2	2	3	3	0	1	0	0	1	3	1
MIL-L-6086 B	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-6387 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-L-644 B	23	3	1	0	3	3	0	0	0	0	1	3	1
MIL-L-7645	23	4	2	0	3	4	0	1	0	0	1	3	1
MIL-L-7808	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-L-7808 F	23	4	1	2	3	3	0	1	0	0	1	3	1
MIL-L-7808 LUBRICANTS	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-L-7870 A	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-L-8383 B	23	4	1	0	1	3	0	1	0	0	1	1	1
MIL-L-9000 F	23	4	1	0	3	4	0	1	0	0	1	3	1
MIL-L-9236 B	23	3	1	0	2	4	0	1	0	0	1	2	1
MIL-O-11773	23	4	1	0	3	3	0	1	0	0	1	3	1
MIL-O-6081 C	23	4	1	0	2	3	0	1	0	0	1	2	1
MIL-P-12098	23	1	2	0	3	4	0	1	0	0	1	3	1

0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
MIL-P-46046 A	23	1	2	0	3	4	0	1	0	0	1	3	1
MIL-R-25576 (RP-1)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-S-3136 B TYPE I	23	4	1	1	2	4	0	1	0	0	1	2	1
MIL-S-3136 B TYPE II	23	4	1	1	3	4	0	1	0	0	1	3	1
MIL-S-3136 B TYPE III	23	4	1	1	3	4	0	1	0	0	1	3	1
MIL-S-3136 B TYPE IV	23	4	1	1	1	3	0	1	0	0	1	1	1
MIL-S-3136 B TYPE V	23	4	1	1	2	3	0	1	0	0	1	2	1
MIL-S-3136 B TYPE VI	23	4	1	1	2	3	0	1	0	0	1	2	1
MIL-S-3136 B TYPE VII	23	4	1	1	3	4	0	1	0	0	1	3	1
MIL-S-3136 TYPE I FUEL (ASTM REFERENCE FUEL A)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-S-3136 TYPE II FUEL	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-S-3136 TYPE III FUEL (ASTM REFERENCE FUEL B)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-S-3136 TYPE IV OIL MEDIUM SWELL	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-S-3136 TYPE IV OIL, HIGH SWELL	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-S-3136 TYPE IV OIL, LOW SWELL	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-S-81087	23	1	1	0	1	4	0	1	0	0	1	1	1
MIL-T-5624 (JP-3, JP-4, JP-5)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-T-83133 (JP-8)	23	0	0	0	0	0	0	0	0	0	1	0	1
MIL-T-9188 B	23	1	4	0	4	4	0	4	0	0	1	4	1
MINE FLUID 3XF	23	0	0	0	0	0	0	0	0	0	1	0	1
MINERAL OIL	23	4	1	1	1	3	0	1	1	1	1	1	1
MIXED ACIDS	23	0	0	0	0	0	0	0	0	0	1	0	1
MLO-7277, 7557	23	0	0	0	0	0	0	0	0	0	1	0	1
MLO-8200, 8515 (MIL-H-8446)	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBAL NIVAC 20, 30	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBIL AMBREX 33	80	4	1	1	3	4	0	1	1	1	1	1	0
MOBIL AMBREX 830	80	4	1	1	1	3	0	1	1	1	1	1	0
MOBIL DELVAC 1100, 1110, 1120, 1130	70	4	1	1	3	4	0	1	1	1	1	1	0
MOBIL DTE25	80	4	1	1	1	4	0	1	1	1	1	1	0
MOBIL HF	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBIL THERM 600	80	4	1	1	4	4	0	1	1	1	1	0	0
MOBIL VACTRA NR.2	80	4	1	1	1	3	0	1	1	1	1	1	0
MOBIL® 254	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBILE JET OIL (MIL-L-23699)	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBILE XRM-206A (MIL-L-83282)	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBILJET II LUBRICANT	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBILJET® II	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBILOIL SAE 20	70	4	1	1	1	4	0	1	1	1	1	1	0
MOBILTHERM® 600	23	0	0	0	0	0	0	0	0	0	1	0	1
MOBILTHERM® 603	23	0	0	0	0	0	0	0	0	0	1	0	1
MOLYDUVAL MOLYKOTE-MINERAL GREASE	50	4	1	1	1	4	0	1	1	1	1	1	0
MOLASSES	23	1	1	1	3	1	0	1	1	1	1	0	0
MOLYBDENUM DISULFIDE GREASE	23	0	0	0	0	0	0	0	0	0	1	0	1
MOLYBDENUM OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
MOLYBDENUM TRIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
MOLYBDIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
MONO BROMOBENZENE	23	4	4	4	4	4	0	1	0	0	1	4	1
MONO BROMOTOLUENE	23	0	0	0	0	0	0	0	0	0	1	0	1
MONO BUTYL PARACRESOL	23	0	0	0	0	0	0	0	0	0	1	0	1
MONO CHLOROACETIC ACID	23	1	4	4	4	4	0	4	0	0	4	4	1
MONO CHLOROACETONE		1	4	4	3	0	0	4	0	0	4	0	0
MONO CHLOROBENZENE	23	4	4	4	4	4	0	1	0	0	1	4	1
MONO CHLOROBUTENE	23	0	0	0	0	0	0	0	0	0	1	0	1
MONO CHLOROHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
MONO ETHANOL AMINE	23	1	4	0	4	2	0	4	0	0	1	4	1
MONO METHYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
MONO METHYL FORMAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
MONOETHANOLAMINE	23	2	4	4	4	3	0	4	0	0	1	4	1
MONOETHYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
MONOISOPROPYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
MONOMETHYL ANILINE	23	2	4	4	4	0	0	2	0	0	1	4	1
MONOMETHYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
MONOMETHYL ETHER (METHYL ETHER) (DIMETHYL ETHER)	23	4	1	0	0	1	0	4	0	0	1	0	1
MONOMETHYL HYDRAZINE	23	1	2	2	0	0	0	0	0	0	1	0	1
MONOMETHYLAMINE (MMA)	23	1	0	0	0	0	0	0	0	0	1	0	1
MONOMETHYLANILINE	23	2	4	4	4	0	0	2	0	0	1	0	1
MONONITROTOLUENE	23	0	0	0	0	0	0	0	0	0	1	0	1
MONOVINYL ACETYLENE	23	2	1	1	0	2	0	1	0	0	1	0	1
MORPHOLINE	23	4	4	4	4	4	0	4	0	0	1	0	1
MOTOR OILS	23	4	1	1	3	3	0	1	1	1	1	1	1
MTBE (METHYL TERT-BUTYL ETHER)	23	0	0	0	0	0	0	0	0	0	1	0	1
MUSTARD	50	1	1	1	1	1	0	1	0	0	1	1	0
MUSTARD GAS	23	1	0	1	3	1	0	1	0	0	1	0	1
MUSTARD OIL	140	0	1	1	0	0	0	1	0	0	1	0	0
MYRICYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
MYRISTIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
MYRISTYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
N,N-DIETHYLANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NAPHTHA	23	4	2	2	3	4	0	1	0	0	1	2	1
NAPHTHALENE	23	4	4	4	2	4	1	1	1	1	1	2	1
NAPHTHALENE CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NAPHTHALENE SULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
NAPHTHENIC ACID	23	4	2	3	4	0	0	1	0	0	1	0	1
NAPHTHYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NATURAL GAS	23	4	1	1	2	4	0	1	1	1	1	2	1
N-BUTYL ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-BUTYL ACRYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-BUTYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
N-BUTYL BUTYRATE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
N-BUTYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-BUTYL METHACRYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-DECANE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-DIBUTYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NEATS FOOT OIL	23	2	1	1	1	2	0	1	0	0	1	1	1
NEOHEXANE		1	1	1	4	0	0	2	0	0	1	0	0
NEON	23	1	1	1	1	1	0	1	1	1	1	0	1
NETATOLUIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NEVILLE ACID	23	2	4	4	0	4	0	1	0	0	1	0	1
N-HEPTANE	23	4	1	1	2	0	0	1	0	0	1	0	1
N-HEXADECANE (CETANE)	23	0	0	0	0	0	0	0	0	0	1	0	1
N-HEXALDEHYDE	23	1	4	4	2	2	0	4	0	0	1	2	1
N-HEXANE	23	4	1	1	2	0	0	1	0	0	1	0	1
N-HEXENE	23	4	2	2	2	4	0	1	0	0	1	2	1
NIACINAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NICKEL ACETATE (AQ)	23	1	3	3	4	4	0	4	1	3	1	4	1
NICKEL AMMONIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
NICKEL CHLORIDE (AQ)	23	1	1	1	3	1	0	1	0	0	1	3	1
NICKEL CYANIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NICKEL NITRATE	23	1	1	0	0	0	0	1	0	0	1	0	1
NICKEL SALTS	23	1	1	1	3	0	0	1	0	0	1	0	1
NICKEL SULFATE (AQ)	23	1	1	1	3	1	0	1	1	3	1	3	1
NICOTINAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NICOTINAMIDE HYDROCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NICOTINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NICOTINE SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITER CAKE	23	1	1	1	1	1	0	1	0	0	1	1	1
NITRIC ACID - RED FUMING (>85%)	23	4	4	4	4	0	0	3	0	0	1	0	1
NITRIC ACID (CONC.)	23	4	4	4	4	0	0	2	0	0	1	0	0
NITRIC ACID (DILUTE)	23	2	4	0	3	2	2	1	0	0	1	3	1
NITRO DILUTION	23	4	4	4	4	4	0	4	0	0	1	4	0
NITROANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROBENZENE	23	1	4	4	4	4	1	2	0	0	1	4	1
NITROBENZOIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROCELLULOSE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROCHLOROBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROCHLOROFORM	23	0	0	0	0	0	0	0	0	0	1	0	1
NITRODIETHYLANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITRODIPHENYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROETHANE	23	2	4	4	4	4	2	4	0	0	1	4	1
NITROFLUOROBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROGEN	23	1	1	1	1	1	0	1	0	0	1	1	1
NITROGEN DIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROGEN OXIDES	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROGEN PEROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
NITROGEN TETROXIDE	23	3	4	4	4	4	0	4	0	0	1	4	1
NITROGEN TRIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROGLYCERINE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROGLYCEROL	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROISOPROPYL BENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROMETHANE	23	2	4	4	4	4	0	4	0	2	1	4	1
NITROPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROPROPANE	23	2	4	4	4	0	0	4	0	0	1	0	1
NITROSYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROSYLSULFURIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROTHIOPHENE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROTOLUENE	23	0	0	0	0	0	0	0	0	0	1	0	1
NITROUS ACID	23	2	4	0	0	0	0	2	0	0	0	0	1
NITROUS OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-OCTADECANE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-OCTANE	23	4	2	2	4	4	0	1	0	0	1	4	1
N-OCTYL ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-OCTYL ALCOHOL (OCTANOL)	23	0	0	0	0	0	0	0	0	0	1	0	1
N-OCTYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
NONANAL	23	0	0	0	0	0	0	0	0	0	1	0	1
NONANE	23	0	0	0	0	0	0	0	0	0	1	0	1
NONYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
NONYL PHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
N-PENTANE	23	4	1	3	3	0	0	1	0	0	1	0	1
N-PROPYL ACETATE	23	2	4	0	4	4	0	4	0	0	1	4	1
N-PROPYL ACETONE	23	1	4	0	4	0	0	4	0	0	1	0	1
N-PROPYL NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-PROPYL PROPIONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-PROPYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-PROPYLBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
N-VALERALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
O-A-548 B	23	1	1	0	3	2	0	2	0	0	1	3	1
OCEANIC HW 443	70	0	1	1	4	0	0	3	0	0	1	4	0
OCEANIC HW 443 (WATER/GLYCOL)	60	0	1	1	4	0	0	3	0	0	1	3	0
OCEANIC HW 540	70	0	1	1	4	0	0	3	0	0	1	3	0
OCEANIC HW 540 (WATER/GLYCOL)	60	0	1	1	4	0	0	3	0	0	1	1	0
O-CHLORO ETHYL BENZENE	23	4	4	4	4	0	0	1	0	0	1	4	1
O-CHLOROANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
O-CHLORONAPHTHALENE	23	1	4	2	4	0	0	4	0	0	1	0	1
O-CHLOROPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
O-CRESOL	23	0	0	0	0	0	0	0	0	0	1	0	1
OCTACHLORONAPHTHALENE	23	0	0	0	0	0	0	0	0	0	1	0	1
OCTACHLOROTOLUENE	23	4	4	0	4	4	0	1	0	0	1	4	1
OCTADECANE	23	4	1	4	1	4	0	1	0	0	1	1	1
OCTADECANOL	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
OCTAFLUOROCYCLOBUTANE	23	0	0	0	0	0	0	0	0	0	1	0	1
OCTANAL	23	0	0	0	0	0	0	0	0	0	1	0	1
OCTANE	23	4	3	3	4	4	0	1	1	1	1	4	1
OCTANONE	23	0	0	0	0	0	0	0	0	0	1	0	1
OCTYL ACETATE	23	1	0	0	4	0	0	4	0	0	1	0	1
OCTYL ALCOHOL	23	3	2	2	4	2	0	1	0	0	1	4	1
OCTYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
OCTYL CRESOL	23	4	3	3	4	4	0	3	0	0	1	0	0
OCTYL PHTHALATE	23	0	0	0	0	0	0	0	0	0	1	0	1
O-DICHLOROBENZENE	23	4	4	0	4	4	0	1	0	0	1	4	1
OIL (AMERICAN LDO SAE 10W30)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (ENGINE EOG-1)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (ENGINE EOG-2)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (ENGINE EOG-3)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (ENGINE EOG-4)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (ENGINE EOG-5)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (ENGINE EOG-6)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (MIL-L-23699)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (MIL-L-8200, MIL-L-2104-B)	23	0	0	0	0	0	0	0	0	0	1	0	1
OIL (MIL-L-83282)	23	0	0	0	0	0	0	0	0	0	1	0	1
OLEFINS	23	0	0	0	0	0	0	0	0	0	1	0	1
OLEIC ACID	23	4	3	1	3	4	1	2	1	1	1	2	1
OLEIN	23	0	0	0	0	0	0	0	0	0	1	0	1
OLEINIC ACID		4	1	1	2	0	0	1	0	0	1	0	0
OLEUM (FUMING SULFURIC ACID)	23	4	4	2	4	0	0	1	0	0	1	0	1
OLEUM SPIRITS	23	4	2	2	3	4	0	1	0	0	1	3	1
OLEYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
OLIVE OIL	23	4	1	1	1	3	0	1	1	1	1	1	1
O-NITROTOLUENE	23	0	0	0	0	0	0	0	0	0	1	0	1
ORANGE ESSENCE	50	4	4	4	0	4	0	3	1	1	1	0	0
ORONITE 8200	23	0	0	0	0	0	0	0	0	0	1	0	1
ORONITE 8515	23	0	0	0	0	0	0	0	0	0	1	0	1
ORONITE HYJET (HYDRAULIC FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
ORONITE HYJET W (HYDRAULIC FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
ORONITE M2V	23	0	0	0	0	0	0	0	0	0	1	0	1
ORTHOPHOS ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
OS-124	23	0	0	0	0	0	0	0	0	0	1	0	1
OS-45 (TYPE III)	23	0	0	0	0	0	0	0	0	0	1	0	1
OS-45 (TYPE IV)	23	0	0	0	0	0	0	0	0	0	1	0	1
O-T-634 B	23	4	3	0	4	4	0	1	0	0	1	4	1
OXALIC ACID	23	1	2	2	4	2	0	1	0	0	1	0	1
OXALIC ACID 25%	23	1	3	3	3	3	0	1	0	3	1	0	0
OXYGEN	23	1	3	1	1	1	0	1	1	1	1	1	1
OXYGEN (COLD)(<100°C)(212°F)	23	1	2	1	1	0	0	1	0	0	1	1	1
OXYGEN (HOT)(>100°C)(212°F)	23	4	4	3	4	0	0	2	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
OXYGEN, LIQUID	23	0	0	0	0	0	0	0	0	0	1	0	1
OZONATED DEIONIZED WATER	23	0	0	0	0	0	0	0	0	0	1	0	1
OZONE	23	1	4	4	1	1	0	1	0	0	1	1	1
OZONE AIR MIXTURE, 50 PPHM OZONE	40	1	4	3	1	1	0	1	3	3	1	1	0
PAINT THINNER, DUCCO	23	4	4	4	4	4	0	2	0	0	1	4	1
PALMITIC ACID (HEXADECANOIC ACID)	23	3	1	1	1	4	0	1	1	1	1	1	1
PARA-AMINOBENZOIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PARA-AMINOSALICYLIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PARA-BROMOBENZYLPHENYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
PARA-CHLOROPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
PARACYMENE	23	0	0	0	0	0	0	0	0	0	0	0	0
PARA-DICHLOROBENZENE	23	4	4	4	4	0	0	1	0	0	1	0	1
PARAFFIN MOLTEN	55	4	1	1	1	3	0	1	1	1	1	1	0
PARAFFIN OIL	50	4	1	1	1	3	0	1	1	1	1	1	0
PARAFFINS	23	1	1	1	4	0	0	1	0	0	1	0	1
PARA-FORMALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PARALDEHYDE	23	1	0	0	3	0	0	0	0	0	4	0	1
PAR-AL-KETONE	23	4	4	0	4	0	0	4	0	0	1	0	1
PARA-NITROANILINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PARA-NITROBENZOIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PARA-NITROPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
PARAPOID 10-C	23	0	0	0	0	0	0	0	0	0	1	0	1
PARATHERM HE	23	0	0	0	0	0	0	0	0	0	1	0	1
PARATHERM NF	23	0	0	0	0	0	0	0	0	0	1	0	1
PARATHION	23	0	0	0	0	0	0	0	0	0	1	0	1
PARA-TOLUENE SULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
P-BENZYLPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
P-CHLOROPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
P-CHLOROTOLUENE	23	0	0	0	0	0	0	0	0	0	1	0	1
P-CYMENE	23	4	4	0	4	4	0	1	0	0	1	4	1
P-D-680	23	4	1	1	3	4	0	1	0	0	1	3	1
P-DICHLOROBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
PEANUT OIL	23	4	1	1	2	1	0	1	1	1	1	2	1
PECTIN (LIQUOR)	23	0	0	0	0	0	0	0	0	0	1	0	1
PELARGONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PENICILLIN	23	1	0	0	0	0	0	0	0	0	1	0	1
PENTACHLORODIPHENYL	n.a.	4	4	4	4	4	0	1	0	0	1	4	0
PENTACHLOROETHANE	23	0	4	0	4	0	0	1	0	0	1	0	1
PENTACHLOROPHENOL	23	3	3	0	4	0	0	1	0	0	1	0	1
PENTADECANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
PENTAERYTHRITOL	23	0	0	0	0	0	0	0	0	0	1	0	1
PENTAERYTHRITOL TETRANITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
PENTALUBE TP-653	23	0	0	0	0	0	0	0	0	0	1	0	1
PENTANE	23	4	1	1	3	4	0	1	0	0	1	0	1
PENTANONE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
PENTOSIN CHF 11S (BRANCH OF AUTOMOBILE)	80	4	1	1	3	4	0	1	1	1	1	1	0
PENTOXOL	23	0	0	0	0	0	0	0	0	0	1	0	1
PENTOXONE	23	0	0	0	0	0	0	0	0	0	1	0	1
PENTYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
PENTYL PENTANOATE	23	0	0	0	0	0	0	0	0	0	1	0	1
PERACETIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PERCHLORIC ACID	23	2	4	4	4	4	0	3	0	0	1	4	1
PERCHLOROETHYLENE	23	4	4	4	4	4	0	1	1	3	1	4	1
PERCHLORYL FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PERFLUOROPROPANE	23	0	0	0	0	0	0	0	0	0	1	0	1
PERFLUOROTRIETHYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PERMANGANIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PERSULFURIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PETROLATUM	23	4	1	1	1	0	0	1	0	0	1	0	1
PETROLATUM ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
PETROLEUM	100	4	3	3	4	4	0	3	0	1	1	3	0
PETROLEUM	23	4	1	1	1	4	0	1	1	1	1	1	0
PETROLEUM ETHER	23	4	1	1	1	4	0	1	1	1	1	0	1
PETROLEUM, Crude	23	0	0	0	0	0	0	0	0	0	0	0	0
PHENOL (CARBOLIC ACID)	23	4	4	4	3	4	1	1	0	0	1	4	1
PHENOL/WATER 70:30 %WEIGHT	50	4	4	4	4	4	0	1	4	4	1	4	0
PHENOLIC SULFONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENOLSULFONIC ACID	23	1	0	0	4	0	0	0	0	0	2	0	1
PHENOXYACETIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYL ACETATE	23	1	0	0	4	0	0	0	0	0	4	0	1
PHENYL ETHYL ETHER	23	4	4	4	4	4	0	4	0	0	1	4	1
PHENYL HYDRAZINE	23	4	4	4	4	4	0	1	0	0	1	4	0
PHENYLACETAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYLACETIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYLBENZENE	23	4	4	4	4	4	0	1	0	0	1	4	1
PHENYLENE DIAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYLETHYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYLETHYL ETHER	23	4	4	4	4	0	0	4	0	0	1	0	1
PHENYLETHYL MOLONIC ESTER	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYLGLYCERINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYLHYDRAZINE	23	4	4	4	0	0	0	1	0	0	1	0	1
PHENYLHYDRAZINE HYDROCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYLMERCURIC ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHENYL METHYLKETONE		1	4	4	4	0	0	4	0	0	4	0	0
PHORONE	23	2	4	4	4	0	0	4	0	0	1	0	1
PHOSGENE	23	1	4	4	4	4	0	4	0	0	2	4	1
PHOSPHATE ESTER		1	4	4	4	0	0	1	0	0	1	0	0
PHOSPHINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHOSPHORIC ACID 20%	23	1	3	3	4	3	0	1	4	4	1	2	1
PHOSPHORIC ACID 3-molar	23	1	4	2	4	0	0	1	0	0	1	0	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
PHOSPHORIC ACID CHLORIDE	23	1	0	0	0	0	0	0	0	0	0	0	0
PHOSPHORIC ACID conc.	23	2	4	4	4	4	0	1	4	4	1	0	0
PHOSPHOROUS OXYLCHLORIDE	23	1	4	4	4	4	0	1	0	0	1	4	0
PHOSPHOROUS TRICHLORIDE	23	1	4	4	4	4	0	1	0	0	1	4	0
PHOSPHORUS (MOLTEN)	23	0	0	0	0	0	0	0	0	0	1	0	1
PHOSPHORUS OXYCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHOSPHORUS PENTAFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PHOSPHORUS TRICHLORIDE	23	1	4	4	0	0	0	1	0	0	1	0	1
PHOTOGRAPHIC FIXER	23	1	1	0	4	1	0	1	1	3	1	0	0
PHTHALIC ACID	23	2	3	0	0	0	0	2	0	0	1	0	1
PHTHALIC ANHYDRIDE	23	1	0	0	0	0	0	0	0	0	2	0	1
PICKLING SOLUTION	23	3	4	0	4	4	0	2	0	0	1	4	1
PICOLINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PICRIC ACID 10%	23	1	1	1	3	4	0	1	3	0	1	0	0
PICRIC ACID AQ.SOL	23	1	2	2	4	4	0	1	3	0	1	0	0
PINE NEEDLE OIL	40	4	1	1	1	4	0	1	1	1	1	1	0
PINE OIL	23	4	4	3	3	4	1	1	0	0	1	0	1
PINE TAR	23	0	0	0	0	0	0	0	0	0	1	0	1
PINENE	23	4	2	2	2	4	0	1	0	0	1	2	1
PIPERAZINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PIPERIDINE	23	4	4	4	4	4	0	4	0	0	1	4	1
PIRANHA	23	0	0	0	0	0	0	0	0	0	1	0	1
PLANTOHYD 40 (GENOL)	80	4	4	4	3	4	0	1	1	3	1	1	0
PLATING SOLUTION-CHROME	23	1	0	4	0	4	0	1	0	0	1	0	1
PLATING SOLUTION-OTHERS	23	1	1	1	0	4	0	1	0	0	1	0	1
P-NITROPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
P-NITROTOLUENE	23	0	0	0	0	0	0	0	0	0	1	0	1
POLYETHYLENE GLYCOL	23	0	0	0	0	0	0	0	0	0	1	0	1
POLYGLYCEROL	23	0	0	0	0	0	0	0	0	0	1	0	1
POLYGLYCOL	23	0	0	0	0	0	0	0	0	0	1	0	1
POLYVINYL ACETATE EMULSION	23	1	0	0	0	0	0	0	0	0	1	0	1
POLYVINYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASH	23	1	1	1	0	0	0	1	0	0	1	0	0
POTASH CAUSTIC 10%	23	1	3	3	3	4	0	3	1	3	1	1	0
POTASSIUM (MOLTEN)	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM ACETATE	23	1	2	4	4	0	0	4	0	0	1	0	1
POTASSIUM ACID SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM ALUM	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM ALUMINUM SULFATE	23	1	1	0	4	0	0	1	0	0	1	0	1
POTASSIUM ANTIMONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM BICARBONATE	23	1	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM BICROMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM BIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM BISULFATE	23	1	1	1	4	0	0	1	0	0	1	0	1
POTASSIUM BISULFITE	23	1	1	1	0	0	0	1	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
POTASSIUM BITARTRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM BORATE, AQ. SOL.	50	1	1	1	0	1	0	1	1	3	1	0	0
POTASSIUM BROMATE, AQ. SOL.	50	1	1	1	3	1	0	1	1	3	1	1	0
POTASSIUM BROMIDE	23	1	1	1	4	1	0	1	1	1	1	0	1
POTASSIUM CARBONATE	23	1	1	1	4	3	0	1	0	0	1	0	1
POTASSIUM CHLORATE	23	1	4	3	4	0	0	1	0	0	1	0	1
POTASSIUM CHLORIDE	23	1	1	1	1	0	0	1	0	0	1	0	1
POTASSIUM CHLORIDE (AQ)	23	1	1	1	3	1	1	1	1	1	1	1	1
POTASSIUM CHROMATE	23	1	1	0	3	0	0	1	0	0	1	0	1
POTASSIUM CITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM COPPER CYANIDE	23	1	1	1	3	0	0	1	0	0	1	0	1
POTASSIUM CUPRO CYANIDE (AQ)	23	1	1	1	1	1	0	1	0	0	1	1	1
POTASSIUM CYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM CYANIDE	23	1	1	1	3	1	0	3	1	0	1	1	1
POTASSIUM DICHROMATE	23	1	1	1	3	1	0	1	1	3	1	1	1
POTASSIUM DIPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM FERRICYANIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
POTASSIUM FERROCYANIDE	23	1	0	0	0	0	0	0	0	0	0	0	0
POTASSIUM FLUORIDE	23	1	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM GLUCOCYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM HYDROXIDE (AQ)	23	1	2	2	4	3	1	4	1	3	1	4	1
POTASSIUM HYPOCHLORITE	23	1	0	0	0	0	0	0	0	0	0	0	1
POTASSIUM IODATE	23	1	0	0	0	0	0	0	0	0	0	0	1
POTASSIUM IODIDE	23	1	1	1	4	0	0	1	0	0	1	0	1
POTASSIUM METABISULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM METASILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM MONOCHROMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM NITRATE	23	1	1	1	3	0	0	1	0	0	1	0	1
POTASSIUM NITRITE	23	1	1	1	3	0	0	1	0	0	1	0	1
POTASSIUM OXALATE	23	1	0	0	0	0	0	0	0	0	0	0	1
POTASSIUM PERCHLORATE	23	1	2	1	4	4	0	1	3	1	1	0	1
POTASSIUM PERFLUOROACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM PERMANGANATE	23	1	4	4	4	0	0	4	1	4	1	2	1
POTASSIUM PEROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM PERSULFATE	23	1	4	1	4	0	0	2	0	0	1	0	1
POTASSIUM PHOSPHATE		1	1	0	0	0	0	1	0	0	1	0	0
POTASSIUM PYROSULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM SALTS	23	1	1	1	1	0	0	1	0	0	1	0	1
POTASSIUM SILICATE	23	1	1	1	0	0	0	1	0	0	1	0	1
POTASSIUM SODIUM TARTRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM STANNATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM STEARATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM SULFATE	23	1	1	1	3	1	0	1	0	0	1	1	1
POTASSIUM SULFIDE	23	1	1	1	0	0	0	1	0	0	1	0	1
POTASSIUM SULFITE	23	1	2	1	4	0	0	1	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
POTASSIUM TARTRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM THIOCYANATE	23	1	0	0	0	0	0	0	0	0	0	0	1
POTASSIUM THIOSULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM TRIPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
POTASSIUM DICHROMATE (AQ)	23	1	1	1	2	1	0	1	0	0	1	2	1
PRESTONE ANTIFREEZE	23	0	0	0	0	0	0	0	0	0	1	0	1
PRODUCER GAS	23	4	1	0	1	2	0	1	0	0	1	1	1
PROPANE	23	4	1	1	3	4	0	1	0	0	1	3	1
PROPANOL	23	1	1	1	4	1	0	1	1	1	1	0	0
PROPIONALDEHYDE	23	1	0	0	3	0	0	0	0	0	4	0	1
PROPIONIC ACID	23	1	3	0	0	0	0	1	0	0	1	0	1
PROPIONITRILE	23	3	2	1	4	0	0	1	0	0	1	0	1
PROPYL ACETATE	23	2	4	4	4	0	0	4	0	0	1	0	1
PROPYL ACETONE (METHYL BUTYL KETONE)	23	1	4	4	4	3	0	4	0	0	1	4	1
PROPYL ALCOHOL (PROPANOL)	23	1	1	1	4	1	1	1	0	0	1	4	1
PROPYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PROPYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
PROPYL NITRATE	23	2	4	4	4	4	0	4	0	0	1	4	1
PROPYL PROPIONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
PROPYLAMINE	23	1	4	4	4	4	0	4	0	0	4	4	1
PROPYLBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
PROPYLENE	23	4	4	4	4	4	0	1	1	1	1	4	1
PROPYLENE CARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
PROPYLENE CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PROPYLENE CHLOROHYDRIN	23	1	0	0	0	0	0	0	0	0	3	0	1
PROPYLENE DICHLORIDE	23	1	0	0	4	0	0	0	0	0	1	0	1
PROPYLENE GLYCOL	23	1	1	1	3	1	0	1	0	0	1	0	1
PROPYLENE IMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PROPYLENE OXIDE	23	2	4	4	4	4	0	4	0	0	1	4	1
PRUSSIC ACID	23	1	3	3	4	4	0	4	4	0	1	4	0
P-S-661 B	23	4	1	0	3	4	0	1	0	0	1	3	1
P-TERT-BUTYLPHENOL	23	0	0	0	0	0	0	0	0	0	1	0	1
P-TERTIARY BUTYL CATECHOL	23	3	4	4	4	0	0	1	0	0	1	4	0
P-TOLUIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PYDRAUL 29EL T, 30E, 50E, 65E, 90E	80	1	4	4	4	3	0	1	0	0	1	4	0
PYDRAUL 312C, 540C	80	4	4	4	4	4	0	1	0	0	1	0	0
PYDRAUL F-9	80	3	4	4	4	0	0	1	0	0	1	0	0
PYDRAUL, 10E, 29 ELT	23	1	4	4	4	4	0	1	0	0	1	4	1
PYDRAUL, 115E	23	1	4	4	4	4	0	1	0	0	1	4	1
PYDRAUL, 230E, 312C, 540C	23	4	4	4	4	4	0	1	0	0	1	4	1
PYDRAUL, 30E, 50E, 65E, 90E	23	1	4	4	4	1	0	1	0	0	1	4	1
PYDRAUI312C, 540C	80	4	4	4	4	4	0	1	0	0	1	0	0
PYRANOL, TRANSFORMER OIL	23	4	1	1	2	4	0	1	0	0	1	2	1
PYRIDINE	23	2	4	4	4	4	0	4	2	1	1	4	1
PYRIDINE SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1

0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
PYRIDINE SULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PYROGALLIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PYROGALLOL	23	1	0	0	0	0	0	0	0	0	1	0	1
PYROGARD 42, 43, 53, 55	23	0	0	0	0	0	0	0	0	0	1	0	1
PYROGARD C&D (WATER&PETROLEUM)	23	0	0	0	0	0	0	0	0	0	1	0	1
PYROLIGNEOUS ACID	23	2	4	4	4	0	0	4	0	0	1	4	1
PYROLUBE	23	0	0	0	0	0	0	0	0	0	1	0	1
PYROSULFURIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
PYROSULFURYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
PYRROLE	23	3	4	4	4	2	0	4	0	0	1	0	1
PYRROLIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
PYRUVIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
Q8 KIRON I T68 (KUWAIT PETROLEUM)	140	4	1	1	4	4	0	1	1	3	1	1	0
QUININE	23	1	0	0	0	0	0	0	0	0	1	0	1
QUININE BISULPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
QUININE HYDROCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
QUININE SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
QUININE TARTRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
QUINIZARIN	23	0	0	0	0	0	0	0	0	0	1	0	1
QUINOLINE	23	0	0	0	0	0	0	0	0	0	1	0	1
QUINONE	23	1	0	0	0	0	0	0	0	0	0	0	1
QUINTOLUBRIC N822 - 220	80	4	4	3	4	4	0	1	1	1	1	1	0
QUINTOLUBRIC N822 - 300	80	4	4	3	3	4	0	1	1	1	1	1	0
QUINTOLUBRIC N850	80	4	4	3	3	4	0	1	1	1	1	1	0
RAPESEED OIL	23	3	2	2	2	4	0	1	0	0	1	2	1
RARE GAS	n.a.	1	1	1	1	3	0	1	1	1	1	1	0
RD-6195	23	0	0	0	0	0	0	0	0	0	1	0	1
RED LINE 100 OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
RED OIL (MIL-H-5606)	23	4	1	1	1	4	0	1	0	0	1	1	1
REFERENCE FUEL A (ISO 1817)	23	4	1	1	1	4	0	1	1	1	1	1	0
REFERENCE FUEL B (ISO 1817)	23	4	3	4	3	4	0	1	1	1	1	3	0
REFERENCE FUEL C (ISO 1817)	23	4	4	4	4	4	0	1	1	1	1	4	0
REFERENCE FUEL D (ISO 1817)	23	4	4	4	4	4	0	1	1	1	1	4	0
RENOLIN MR 20 VG 68 (FUCHS)	80	4	1	1	1	3	0	1	1	1	1	1	0
RESORCINOL	23	0	0	0	0	0	0	0	0	0	1	0	1
RHODIUM	23	0	0	0	0	0	0	0	0	0	1	0	1
RIBOFLAVIN	23	0	0	0	0	0	0	0	0	0	1	0	1
RICINOLEIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
RJ-1 (MIL-F-25558 B)	23	4	1	1	1	4	0	1	0	0	1	1	1
RJ-4 (MIL-F-82522)	23	0	0	0	0	0	0	0	0	0	1	0	1
ROSIN	23	0	0	0	0	0	0	0	0	0	1	0	1
ROYCO 808-RH	23	0	0	0	0	0	0	0	0	0	1	0	1
ROYCO 899 (MIL-L-23699)	23	0	0	0	0	0	0	0	0	0	1	0	1
RP-1 (MIL-F-25576 C)	23	4	1	1	1	4	0	1	0	0	1	1	1
SACCHAROSE SOLUTION	23	1	1	1	4	0	0	1	0	0	1	0	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
SAL AMMONIAC	23	1	1	1	3	2	0	1	0	0	1	1	1
SALICYLIC ACID	23	1	2	2	4	0	0	1	0	0	1	0	1
SALT SOLUTION	50	1	1	1	3	1	0	1	1	3	1	1	0
SALT WATER	23	1	1	1	2	1	0	1	0	0	1	2	1
SANTOSAFE 300	23	0	0	0	0	0	0	0	0	0	1	0	1
SATFA EC-3686 (TRANSMISSION FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
SAUERKRAUT	23	1	1	1	4	1	0	3	1	3	1	1	0
SC-1 (STANDARD CLEAN-1)	23	0	0	0	0	0	0	0	0	0	1	0	1
SC-2 (STANDARD CLEAN-2)	23	0	0	0	0	0	0	0	0	0	1	0	1
SEAWATER	23	1	1	1	4	1	0	1	1	3	1	1	0
SEBACIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
SEC-BUTYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
SECONDARY BUTYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
SELENIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
SELENOUS ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
SERVICE FLUID 101	23	0	0	0	0	0	0	0	0	0	1	0	1
SEWAGE	23	2	1	1	4	2	0	1	1	3	1	4	1
SHELL AIR (GG1034 WTR)	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL AIR TURBINE OIL NO. 505 (MIL-L-23699)	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL ALVANIA R 2 (MINERAL-GREASE)	60	4	1	1	1	3	0	1	1	1	1	1	0
SHELL DIALA-QL D	80	4	1	1	1	4	0	1	1	1	1	1	0
SHELL DROMUS OIL B	60	4	1	1	4	4	0	1	1	3	1	1	0
SHELL F.R. FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL FIREGARD 200	60	1	1	1	4	2	0	3	1	3	1	2	0
SHELL HSG 80W/90 (BRANCH OF AUTOMOBILE)	80	4	1	1	1	4	0	1	1	1	1	1	0
SHELL HYDROL DO 46	80	4	1	1	1	3	0	1	1	1	1	1	0
SHELL IRIS 902	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL MACOMA 72	80	4	1	1	1	4	0	1	1	1	1	1	0
SHELL NATURELLE HF-E 15	80	4	4	4	4	4	0	1	1	1	1	1	0
SHELL OMALA 68	80	4	1	1	1	3	0	1	1	1	1	1	0
SHELL ROTELLA T 15W40 DIESEL OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL SPIRAX EP90	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL SPIRAX HD (REAR AXLE ADDITIVE)	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL SUPER OIL (STP OIL ADDITIVE)	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL TELL US 27,33	80	4	1	1	1	4	0	1	1	1	1	1	0
SHELL TELL US 68	80	4	1	1	1	4	0	1	1	1	1	1	0
SHELL TELL US 68 + 5% CASTROL CX 23	80	4	1	1	3	4	0	1	1	1	1	1	0
SHELL TELL US T 37	80	4	1	1	1	4	0	1	1	1	1	1	0
SHELL TIRENA WA	80	4	1	1	1	3	0	1	1	1	1	1	0
SHELL TMO SW 30	80	4	4	4	4	4	0	1	1	1	1	1	0
SHELL TURBINE N0.307	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELL UMF (5% AROMATIC)	23	0	0	0	0	0	0	0	0	0	1	0	1
SHELLAC	23	0	0	0	0	0	0	0	0	0	1	0	1
SHINOL TWS-R	23	0	0	0	0	0	0	0	0	0	1	0	1
SIDERLUBRIC 822-200	80	4	4	3	4	4	0	1	1	1	1	1	0

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
SILANE	23	0	0	0	0	0	0	0	0	0	1	0	1
SILICATE ESTERS	23	4	2	2	3	4	0	1	0	0	1	1	1
SILICON TETRACHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SILICON TETRAFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SILICONE FLUORHYDROGEN	23	1	2	0	4	0	0	1	0	0	1	0	0
SILICONE FLUORIC ACID	23	2	2	2	0	0	0	2	0	0	1	0	0
SILICONE GREASES	23	1	1	1	1	3	0	1	0	0	1	1	1
SILICONE OILS	23	1	1	1	1	3	0	1	0	0	1	1	1
SILICONE TETRACHLORIDE	23	2	0	0	0	0	0	0	0	0	1	0	1
SILVER BROMIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
SILVER CHLORIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
SILVER CYANIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
SILVER NITRATE	23	1	2	2	3	1	0	1	1	3	1	1	1
SILVER SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SINCLAIR OPALINE CX-EP LUBE	23	0	0	0	0	0	0	0	0	0	1	0	1
SKYDROL 500	23	1	4	4	4	3	2	4	0	0	1	4	1
SKYDROL 500 B4 (MONSANTO)	70	1	4	4	4	4	0	4	0	1	1	4	0
SKYDROL 7000	23	1	4	4	4	3	0	2	0	0	1	4	1
SKYDROL LD4 (7000) (MONSANTO)	70	1	4	4	4	4	0	4	0	1	1	4	0
SKYLUBE 450	23	0	0	0	0	0	0	0	0	0	1	0	1
SOAP SOLUTIONS	23	1	1	1	3	1	0	1	0	0	1	3	1
SOC-100 (SAE 10W40 SYNTHETIC ENGINE OIL)	23	0	0	0	0	0	0	0	0	0	1	0	1
SOCONY PD959B VACUUM	23	0	0	0	0	0	0	0	0	0	1	0	1
SODA ASH	23	1	1	1	0	1	0	1	0	0	1	0	1
SODIUM (MOLTEN)	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ACETATE (AQ)	23	1	3	3	4	4	0	4	1	3	1	4	1
SODIUM ACID BISULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ACID FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ACID SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ALUMINATE	23	1	0	0	1	0	0	1	0	0	1	0	1
SODIUM ALUMINATE SULFATE	23	0	1	1	0	0	0	1	0	0	1	0	1
SODIUM ANTHRAQUINONE DISULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ANTIMONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ARSENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ARSENITE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM BENZOATE	23	1	1	1	4	1	0	1	1	3	1	0	1
SODIUM BICARBONATE	23	1	1	1	4	1	0	1	0	0	1	0	1
SODIUM BICHROMATE	23	1	1	1	4	0	0	1	0	0	1	0	1
SODIUM BIFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM BISULFATE	23	1	1	1	0	0	0	1	0	0	1	0	1
SODIUM BISULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM BISULFITE	23	1	3	1	4	0	0	1	0	0	1	0	1
SODIUM BISULFITE (AQ)	23	1	1	1	3	1	1	1	0	3	1	1	1
SODIUM BITARTRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM BORATE (AQ)	23	1	1	1	3	1	1	1	1	3	1	1	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
SODIUM BROMATE	23	1	0	0	0	0	0	1	0	0	1	0	1
SODIUM BROMIDE	23	1	0	0	0	0	0	1	0	0	1	0	1
SODIUM CARBONATE	23	1	1	1	4	1	0	1	1	3	1	0	1
SODIUM CHLORATE	23	1	2	1	3	4	0	1	1	3	1	0	1
SODIUM CHLORIDE	23	1	1	1	1	0	0	1	0	0	1	0	1
SODIUM CHLORIDE (AQ)	23	1	1	1	3	1	1	1	1	3	1	1	1
SODIUM CHLORITE	23	4	4	0	0	0	0	4	0	0	2	0	1
SODIUM CHLOROACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM CHROMATE	23	1	1	1	4	0	0	1	0	0	1	0	1
SODIUM CITRATE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM CYANAMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM CYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM CYANIDE (AQ)	23	1	1	1	3	1	0	1	1	3	1	1	1
SODIUM DIACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM DICHROMATE	23	1	1	1	4	3	0	1	0	3	1	1	1
SODIUM DIPHENYL SULFONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM DIPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM DISILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM ETHYLATE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM FERRICYANIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM FERROCYANIDE	23	1	0	0	0	0	0	0	0	0	1	0	1
SODIUM FLUORIDE	23	1	1	0	0	0	0	1	0	0	1	0	1
SODIUM FLUOSILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM GLUTAMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM HYDRIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM HYDROGEN SULFATE	23	1	1	1	0	0	0	1	0	0	1	0	1
SODIUM HYDROSULFIDE	23	1	1	1	4	0	0	1	0	0	1	0	1
SODIUM HYDROSULFITE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM HYDROXIDE (AQ)	23	1	3	3	4	2	1	2	3	3	1	4	1
SODIUM HYDROXIDE 10% (CAUSTIC SODA)	50	1	3	3	4	4	0	3	3	3	1	3	0
SODIUM HYDROXIDE 25% (CAUSTIC SODA)	50	1	3	3	4	4	0	4	3	3	1	3	0
SODIUM HYPOCHLORITE (AQ) (CHLOROX)	23	2	3	3	4	2	1	2	4	4	1	3	1
SODIUM HYPOPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM HYPOPHOSPHITE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM HYPOSULFITE	23	1	2	0	3	0	0	1	0	0	1	0	1
SODIUM IODIDE	23	1	0	0	0	0	0	1	0	0	1	0	1
SODIUM LACTATE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM METAPHOSPHATE	23	1	1	1	0	0	0	1	0	0	1	0	1
SODIUM METASILICATE	23	1	0	0	0	0	0	0	0	0	1	0	1
SODIUM METHYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM MONOPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM NITRATE	23	1	2	1	4	0	0	1	0	0	1	0	1
SODIUM NITRITE, AQ. SOL.	50	1	2	1	4	1	0	1	1	3	1	0	1
SODIUM OLEATE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM ORTHOSILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
SODIUM OXALATE	23	1	1	0	0	0	0	1	0	0	1	0	1
SODIUM PERBORATE	23	1	3	3	4	3	0	1	1	0	1	1	1
SODIUM PERCARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM PERCHLORATE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM PEROXIDE	23	1	2	2	4	4	0	1	0	0	1	4	1
SODIUM PERSULFATE	23	1	0	0	0	0	0	1	0	0	1	0	1
SODIUM PHENOLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM PHENOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM PHOSPHATE (AQ)	23	1	1	1	1	4	1	1	0	0	1	1	1
SODIUM PHOSPHATE, (DIBASIC)	23	1	1	1	3	0	0	1	0	0	1	0	1
SODIUM PHOSPHATE, (MONOBASIC)	23	1	1	1	3	0	0	1	0	0	1	0	1
SODIUM PHOSPHATE, (TRIBASIC)	23	1	1	1	3	0	0	1	0	0	1	0	1
SODIUM PLUMBITE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM PYROPHOSPHATE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM RESINATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM SALICYLATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM SALTS	23	1	1	1	1	0	0	1	0	0	1	0	1
SODIUM SESQUISILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM SILICATE (AQ)	23	1	1	1	4	0	1	1	0	0	1	0	1
SODIUM SILICOFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM STANNATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM STEARATE, AQ. SOL.	50	1	1	1	0	1	0	1	0	0	1	0	0
SODIUM SULFATE (AQ)	23	1	1	1	3	1	1	1	1	3	1	1	1
SODIUM SULFIDE	23	1	2	1	3	1	0	2	1	3	1	1	1
SODIUM SULFITE	23	1	1	1	1	0	0	1	0	0	1	0	1
SODIUM SULFOCYANIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM TARTRATE	23	1	0	0	0	0	0	0	0	0	0	0	1
SODIUM TETRABORATE	23	1	2	1	3	0	0	1	0	0	1	0	0
SODIUM TETRAPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM TETRASULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM THIOARSENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM THIOCYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM THIOSULFATE (AQ)	23	1	2	1	3	1	0	1	1	3	1	1	1
SODIUM TRICHLOROACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM TRIPHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
SODIUM, LIQUID	23	0	0	0	0	0	0	0	0	0	1	0	1
SOLVASOL 1, 2, 3	23	0	0	0	0	0	0	0	0	0	1	0	1
SOLVESSO 100, 150	23	0	0	0	0	0	0	0	0	0	1	0	1
SORBITOL	23	0	0	0	0	0	0	0	0	0	1	0	1
SOUP SOLUTION	50	1	1	1	4	1	0	1	1	3	1	1	0
SOUR CRUDE OIL	23	4	2	2	2	0	0	2	0	0	1	0	1
SOUR MILK	50	1	1	1	4	1	0	1	1	3	1	1	0
SOUR NATURAL GAS	23	4	2	2	3	0	0	2	0	0	1	0	1
SOYA OIL	50	3	1	1	2	4	0	1	1	1	1	1	0
SPIRAX 90 EP OIL (STP ADDITIVE)	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
SPIRITS, SCHNAPS	23	1	1	1	4	1	0	1	1	1	1	2	0
SR10 FUEL	23	0	0	0	0	0	0	0	0	0	1	0	1
SR6 FUEL	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNIC AMMONIUM CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNIC CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNIC CHLORIDE (AQ)	23	1	1	1	0	2	0	1	0	0	1	0	1
STANNIC TETRACHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNOUS BISULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNOUS BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNOUS CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNOUS CHLORIDE (AQ)	23	1	1	1	0	2	0	1	0	0	1	0	1
STANNOUS FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STANNOUS SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
STARCH		1	1	1	4	1	0	1	0	0	1	1	0
STAUFFER 7700	23	4	2	2	0	0	0	1	0	0	1	0	1
STAUFFER JET II (MIL-L-23699B)	23	0	0	0	0	0	0	0	0	0	1	0	1
STEAM UP TO 150°C		1	4	1	4	0	1	0	0	0	1	4	0
STEAM UP TO 175°C		1	4	3	4	0	1	0	0	0	1	4	0
STEAM UP TO 200°C		4	4	4	4	0	1	0	0	0	1	4	0
STEAM UP TO 260°C		4	4	4	4	0	3	0	0	0	1	4	0
STEARIC ACID	23	3	3	2	3	4	0	2	1	1	1	1	1
STEARYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
STERILE WATER-FOR-INJECTION	23	0	0	0	0	0	0	0	0	0	1	0	1
STODDARD SOLVENT (ASTM D-484-52)	23	4	1	1	1	0	0	1	0	0	1	0	1
STRONTIUM ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1
STRONTIUM CARBONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
STRONTIUM CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STRONTIUM HYDROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
STRONTIUM NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
STYRENE	23	4	4	4	3	4	2	2	0	0	1	3	1
SUBERIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
SUCCINALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SUCCINIC ACID	23	1	1	0	4	0	0	1	0	0	1	0	1
SUCROSE SOLUTION	23	1	1	2	4	1	0	1	0	0	1	4	1
SULFAMIC ACID	23	1	0	0	2	0	0	0	0	0	0	0	1
SULFANILIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFANILIC CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFANILIMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFINOL	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFITE LIQUORS	23	2	2	0	0	4	0	1	0	0	1	0	1
SULFOLANE	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFOLE	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFUR	23	1	4	4	0	3	0	1	0	0	1	0	1
SULFUR CHLORIDE (AQ)	23	4	3	4	4	3	0	1	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
SULFUR DIOXIDE (DRY)	23	1	4	4	4	2	2	3	4	1	1	0	1
SULFUR DIOXIDE (LIQUIFIED UNDER PRESSURE)	23	1	4	4	0	2	0	2	0	0	1	0	1
SULFUR DIOXIDE (WET)	23	1	4	4	4	2	0	2	4	2	1	0	1
SULFUR HEXAFLUORIDE	23	1	2	2	3	2	0	3	1	1	1	0	1
SULFUR MONOCHLORIDE	23	4	4	4	4	0	0	1	0	0	1	0	1
SULFUR TETRAFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFUR TRIOXIDE	23	2	4	4	4	2	0	1	0	0	1	0	1
SULFUR, MOLTEN	23	3	4	0	4	0	0	1	0	0	1	0	1
SULFURIC ACID (20% OLEUM)	23	4	4	2	4	4	1	1	0	0	1	4	1
SULFURIC ACID (CONC.)	23	3	4	4	4	4	1	1	0	0	1	4	1
SULFURIC ACID (DILUTE)	23	2	3	0	3	4	1	1	0	0	1	2	1
SULFURIC ACID (FUMING)	23	4	4	4	4	0	0	3	0	0	1	0	0
SULFURIC CHLOROHYDRIN	23	0	0	0	0	0	0	0	0	0	1	0	1
SULFUROUS ACID	23	2	3	3	3	4	0	3	4	2	1	3	1
SULFURYL CHLORIDE	23	1	0	0	2	0	0	0	0	0	1	0	1
SULPHONATED OILS	23	0	0	0	0	0	0	0	0	0	1	0	1
SULPHONYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
SUN XSC 71 367 OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
SUNFLOWER OIL	80	4	1	1	1	1	0	1	1	1	1	1	0
SUNOCO SAE 10	23	0	0	0	0	0	0	0	0	0	1	0	1
SUNOCO SUNOMATIC 136 ATF	23	0	0	0	0	0	0	0	0	0	1	0	1
SUNOCO SUNOMATIC 141 ATF	23	0	0	0	0	0	0	0	0	0	1	0	1
SUNOCO X5 820 LUBE	23	0	0	0	0	0	0	0	0	0	1	0	1
SUPER 284 OS19381 (TRANSMISSION FLUID)	23	0	0	0	0	0	0	0	0	0	1	0	1
SUPERMIL ASU-06752	23	0	0	0	0	0	0	0	0	0	1	0	1
SUPERSHELL GASOLINE	23	0	0	0	0	0	0	0	0	0	1	0	1
SUVA 134a	23	0	0	0	3	0	0	0	1	1	1	3	0
SUVA 9000	23	0	0	0	3	0	0	0	1	1	1	3	0
SUVA HP62	23	0	0	0	1	0	0	0	1	1	1	1	0
SWANFINCH EP LUBRICANT	23	0	0	0	0	0	0	0	0	0	1	0	1
SYM-DIPHENYLETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
TAE (TERT-AMYL ETHYL ETHER)	23	0	0	0	0	0	0	0	0	0	1	0	1
TALLOW	23	0	0	0	0	0	0	0	0	0	1	0	1
TANNIC ACID	23	1	1	1	1	2	0	1	3	0	1	1	1
TANNIN		1	2	1	3	0	0	1	0	0	1	0	0
TAR, BITUMINOUS	23	3	2	2	0	2	0	1	0	0	1	0	1
TAR, TAR OIL	23	4	4	4	3	4	0	1	1	1	1	1	0
TARTARIC ACID	23	2	1	1	1	1	0	1	0	0	1	1	1
TEBIOL HVI 32 A	80	4	4	4	4	4	0	1	1	1	1	1	0
TEL-4081	23	0	0	0	0	0	0	0	0	0	1	0	1
TELLONE® II	23	0	0	0	0	0	0	0	0	0	1	0	1
TEOS	23	0	0	0	0	0	0	0	0	0	1	0	1
TEREPHTHALIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
TERPINEOL	23	2	3	2	3	0	0	2	0	0	1	2	1
TERPINYL ACETATE	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
TERT-AMYL ETHYL ETHER (TAEE)	23	0	0	0	0	0	0	0	0	0	1	0	1
TERT-AMYL METHYL ETHER (TAME)	23	0	0	0	0	0	0	0	0	0	1	0	1
TERTIARY BUTYL ALCOHOL	23	2	2	2	4	2	1	1	0	0	1	4	1
TERTIARY BUTYL CATECHOL	23	2	4	0	4	0	0	1	0	0	1	4	1
TERTIARY BUTYL MERCAPTAN	23	4	4	4	4	4	0	1	0	0	1	4	1
TETRABROMOETHANE	23	4	4	4	0	4	0	1	0	0	1	0	1
TETRABROMOMETHANE	23	1	4	2	4	0	0	4	0	0	1	0	1
TETRABUTYL TITANATE	23	1	2	2	0	0	0	1	0	0	1	0	1
TETRACHLORODIFLUORETHANE		1	2	2	4	0	0	1	0	0	1	0	0
TETRACHLOROETHANE	23	4	4	4	4	0	0	1	0	0	1	0	1
TETRACHLOROETHYLENE	23	4	4	4	4	4	4	1	0	0	1	4	1
TETRACHLOROMETHANE	23	4	3	3	3	4	0	1	3	1	1	3	0
TETRADECANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRAETHYL LEAD	23	4	2	2	4	0	0	1	0	4	1	0	1
TETRAETHYLENGLYCOL (TEG)	23	1	0	0	1	0	0	0	0	0	1	0	0
TETRAETHYLORTHOSILICATE (TEOS)	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRAFLUOROETHYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRAFLUOROMETHANE (F-14)	23	1	1	1	1	0	0	1	0	0	1	0	1
TETRAHYDROFURAN (THF)	23	3	4	4	3	4	0	4	3	2	1	3	1
TETRALIN (TETRAHYDRONAPHTHALENE)	23	4	4	4	3	0	0	1	0	0	1	0	1
TETRAMETHYL AMMONIUM HYDROXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRAMETHYLCYCLOTETRASILOXANE (TMCTS)	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRAMETHYLDIHYDROPYRIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRANITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRAPHOSPHOGLUCOSATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TETRAPHOSPHORIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXACO 3450 GEAR OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXACO REGAL B	70	4	1	1	1	4	0	1	1	1	1	1	0
TEXACO TL-8262B ATF	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXACO UNI-TEMP	23	4	1	1	1	3	0	1	1	1	1	1	0
TEXACO UNI-TEMP GREASE	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXAMATIC "A" TRANSMISSION-OIL	23	4	1	1	3	4	0	1	1	1	1	0	0
TEXAMATIC 1581 FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXAMATIC 3401 FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXAMATIC 3525 FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXAMATIC 3528 FLUID	23	0	0	0	0	0	0	0	0	0	1	0	1
TEXTILE CLEANERS		4	3	3	4	0	0	1	0	0	1	0	0
THERMINOL 44/45	23	0	0	0	0	0	0	0	0	0	1	0	1
THERMINOL® 55	23	0	0	0	0	0	0	0	0	0	1	0	1
THERMINOL® 66	23	0	0	0	0	0	0	0	0	0	1	0	1
THERMINOL® FR	23	0	0	0	0	0	0	0	0	0	1	0	1
THINNER		4	4	4	4	0	0	2	0	0	1	0	0
THIO ACID CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
THIOAMYL ALCOHOL	23	0	0	0	0	0	0	0	0	0	1	0	1
THIODIACETIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
THIOETHANOL	23	0	0	0	0	0	0	0	0	0	1	0	1
THIOFURAN	23	0	0	0	0	0	0	0	0	0	1	0	1
THIOGLYCOLIC ACID	23	1	0	0	0	0	0	0	0	0	0	0	1
THIOKOL TP-90 B	23	1	4	4	0	0	0	1	0	0	1	0	0
THIOKOL TP-95	23	1	4	4	0	0	0	1	0	0	1	0	0
THIONYL CHLORIDE	23	3	4	4	4	4	0	2	0	0	1	4	1
THIOPHENE	23	1	0	0	4	0	0	0	0	0	3	0	1
THIOPHOSPHORYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
THIOUREA	23	0	0	0	0	0	0	0	0	0	1	0	1
THORIUM NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TIN AMMONIUM CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TIN(II) CHLORIDE 15%	23	1	1	1	4	0	0	1	0	0	1	0	0
TIN(IV) CHLORIDE	23	1	1	1	4	0	0	1	0	0	1	0	0
TIN(IV)CHLORIDE 50%	23	1	1	1	4	0	0	1	0	0	1	0	0
TITANIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
TITANIUM DIOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TITANIUM SULFATE	23	1	0	0	0	0	0	0	0	0	0	0	1
TITANIUM TETRACHLORIDE	23	4	2	2	4	4	0	1	0	0	1	4	1
TOK 105 STRIPPER	23	0	0	0	0	0	0	0	0	0	1	0	1
TOK 106 STRIPPER	23	0	0	0	0	0	0	0	0	0	1	0	1
TOLUENE	23	4	4	4	4	4	4	2	1	1	1	4	1
TOLUENE BISODIUM SULFITE	23	0	0	0	0	0	0	0	0	0	1	0	1
TOLUENE DIISOCYANATE (TDI)	23	2	4	4	4	4	0	4	0	0	1	4	1
TOLUENE SULPHFONYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TOLUENE/PYRIDINE (95%/5%)	23	0	0	0	0	0	0	0	0	0	1	0	1
TOLUENESULPHONIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
TOLUIDINE	23	1	0	0	0	0	0	0	0	0	2	0	1
TOLUQUINONE	23	0	0	0	0	0	0	0	0	0	1	0	1
TOLUYLENE DIISOCYANATE	23	3	4	4	4	4	0	3	0	0	1	4	0
TOLYLALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TOOTHPASTE	50	1	1	1	0	1	0	1	1	1	1	0	0
TRAIN OIL		4	1	1	2	0	0	1	0	0	1	0	0
TRANSFORMER OIL	23	4	1	1	1	2	0	1	0	0	1	1	1
TRANSMISSION FLUID (ATF 1)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRANSMISSION FLUID (ATF 2)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRANSMISSION FLUID (ATF 3)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRANSMISSION FLUID (ATF 4)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRANSMISSION FLUID (ATF 5)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRANSMISSION FLUID (FORD)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRANSMISSION FLUID TYPE A		4	1	1	1	0	0	1	0	0	1	0	0
TRANSMISSION FLUID TYPE A	23	4	1	1	1	2	0	1	0	0	1	1	1
TREFLAN	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIACETIN	23	1	2	2	4	1	0	4	0	0	1	4	1
TRIALKYLPHOSPHATE	23	2	4	4	4	0	0	4	0	0	1	0	0
TRIARYL PHOSPHATE	23	1	4	4	4	3	0	1	0	0	1	4	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
TRIBROMOMETHYLBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIBUTOXETHYL PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIBUTOXY ETHYL PHOSPHATE	23	1	4	4	4	0	0	1	0	0	1	4	1
TRIBUTYL CITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIBUTYL MERCAPTAN	23	4	4	3	4	4	0	1	0	0	1	0	1
TRIBUTYL PHOSPHATE	23	2	4	4	4	4	1	4	0	0	1	4	1
TRIBUTYLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRICHLOROACETIC ACID	23	2	3	3	4	4	0	4	4	4	1	4	0
TRICHLOROACETYL CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRICHLOROBENZENE	23	1	0	0	4	0	0	0	0	0	2	0	1
TRICHLOROETHANE	23	4	4	4	4	4	0	1	3	0	1	4	0
TRICHLOROETHANOLAMINE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRICHLOROETHYLENE (TCE)	23	4	4	4	4	4	0	1	4	2	1	4	1
TRICHLOROFLUOROMETHANE (F-11)	23	4	2	0	4	0	0	2	0	0	1	0	1
TRICHLOROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRICHLORONITROMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRICHLOROPHENYLSILANE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRICHLOROPROPANE (1,2,3-)	23	1	0	0	4	0	0	0	0	0	2	0	1
TRICHLOROSILANE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRICHLOROTRIFLUOROETHANE (F-113, TF)	23	3	1	0	2	0	0	2	0	0	1	0	1
TRICRESYL PHOSPHATE	23	2	4	4	4	3	1	1	1	1	1	4	1
TRIDECANOL		0	1	0	0	0	0	1	0	0	1	0	0
TRIETHANOLAMINE (TEA)	23	2	3	3	4	4	0	3	1	1	1	4	0
TRIETHYL PHOSPHATE	23	1	0	0	0	0	0	0	0	0	4	0	1
TRIETHYLALUMINIUM	23	3	4	0	4	0	0	2	0	0	1	4	1
TRIETHYLAMINE	23	4	3	3	3	0	0	2	0	0	1	0	1
TRIETHYLBORANE	23	1	4	0	0	0	0	0	0	0	1	0	1
TRIETHYLENE GLYCOL (TEG)	23	1	1	0	0	0	0	1	0	0	1	0	1
TRIETHYLENE TETRAMINE (TETA)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIFLUOROACETIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIFLUOROCHLOROETHYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIFLUOROETHANE		4	4	4	4	0	0	1	0	0	1	0	0
TRIFLUOROMETHANE (FLUOROFORM, F-23)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIFLUOROTOLUENE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIFLUOROVINYLCHELORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIISOCYANATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIISODOMETHANE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIISOPROPYLBENZYLCHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIMETHYL BORATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIMETHYL PHOSPHITE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIMETHYLALUMINIUM (TMAL)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIMETHYLAMINE (TMA)	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIMETHYLBENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIMETHYLENE BROMIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIMETHYLOLPROPANE DIALLYL ETHER (TMPDE)	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
TRIMETHYLPENTANE	23	4	1	1	2	0	0	1	0	0	1	0	1
TRINITROTOLUENE (TNT)	23	4	4	4	4	4	0	2	0	0	1	4	1
TRIOCTYL PHOSPHATE	23	1	4	4	4	3	0	2	0	0	1	4	1
TRIOXANE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIPHENYLPHOSPHITE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRIPOTASSIUM PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRISODIUM PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
TRITIUM	23	0	0	0	0	0	0	0	0	0	1	0	1
TT-I-735 B	23	1	1	1	2	1	0	1	0	0	1	2	1
TT-N-95 A	23	4	1	1	3	4	0	1	0	0	1	3	1
TT-N-97 B	23	4	1	1	3	4	0	1	0	0	1	3	1
TT-S-735 TYPE I	23	4	1	1	2	4	0	1	0	0	1	2	1
TT-S-735 TYPE II	23	4	1	1	3	4	0	1	0	0	1	3	1
TT-S-735 TYPE III	23	4	1	1	3	4	0	1	0	0	1	3	1
TT-S-735 TYPE IV	23	4	1	1	1	3	0	1	0	0	1	1	1
TT-S-735 TYPE V	23	4	1	1	2	3	0	1	0	0	1	2	1
TT-S-735 TYPE VI	23	4	1	1	2	3	0	1	0	0	1	2	1
TT-S-735 TYPE VII	23	4	1	1	3	4	0	1	0	0	1	3	1
TT-T-656B	23	1	4	0	4	4	0	4	0	0	1	4	1
TUNG OIL (CHINA WOOD OIL)	23	3	1	1	3	4	0	1	0	0	1	3	1
TUNGSTEN HEXAFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
TUNGSTIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
TURBINE OIL	23	4	2	1	1	4	0	1	0	0	1	1	1
TURBO NO. 10 OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
TURBO NO. 65 OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
TURBO NO. P-16 OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
TURPENTINE	23	4	2	2	4	4	3	1	1	1	1	4	1
UCON 300N (LUBRICANTS 50-HB-280X)	23	0	0	0	0	0	0	0	0	0	1	0	1
UCON HYDROLUBE J-4	23	0	0	0	0	0	0	0	0	0	1	0	1
UCON OIL LB-385, 400X	23	0	0	0	0	0	0	0	0	0	1	0	1
UCON® LUBRICANTS/FLUIDS	23	0	0	0	0	0	0	0	0	0	1	0	1
UDMH (UNSYMMETRICAL DIMETHYL HYDRAZINE)	23	1	2	2	4	4	0	4	0	0	1	0	1
UNDECYCLIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
UNDECYCLIC ACID	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIFLEX 103	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIFLEX 186	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIFLEX 211	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIFLEX 212	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIFLEX 215	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIFLEX 31	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIFLEX 33	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIVIS 40 (ESSO)	70	4	1	1	1	4	0	1	1	1	1	1	0
UNIVIS J 13 (ESSO)	80	4	1	1	1	4	0	1	1	1	1	1	0
UNIVIS J-43	23	0	0	0	0	0	0	0	0	0	1	0	1
UNIVOLT NO.35 (MINERAL OIL)	23	0	0	0	0	0	0	0	0	0	1	0	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
UNSYMMETRICAL DIMETHYL HYDRAZINE	23	0	0	0	0	0	0	0	0	0	1	0	1
UPDI (ULTRA PURE DEIONIZED WATER)	23	0	0	0	0	0	0	0	0	0	1	0	1
URANIUM HEXAFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
URANIUM SULFATE	23	0	0	0	0	0	0	0	0	0	1	0	1
UREA	23	1	2	0	0	0	0	1	0	0	1	0	1
UREA, AQ. SOL.	50	1	1	1	3	3	0	1	1	1	1	0	0
URIC ACID	23	1	0	0	0	0	0	0	0	0	0	0	1
VACUUM PUMP OIL N 62 (LEYBOLD)	80	4	3	1	1	1	0	1	1	1	1	1	0
VALERALDEHYDE	23	0	0	0	0	0	0	0	0	0	1	0	1
VALERIC ACID	23	1	0	0	0	0	0	0	0	0	0	0	1
VANADIUM OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
VANADIUM PENTOXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
VANILLA EXTRACT	23	0	0	0	0	0	0	0	0	0	1	0	1
VARNISH	23	4	2	2	3	4	0	1	0	0	1	3	1
VASELINE	40	4	1	1	1	1	0	1	1	1	1	1	0
VEEDOL HYPOID OIL	23	0	0	0	0	0	0	0	0	0	1	0	1
VEGETABLE OIL	23	3	1	1	1	2	0	1	1	1	1	1	1
VERMAN	23	0	0	0	0	0	0	0	0	0	1	0	1
VERSILUBE F44, F50, F55	23	0	0	0	0	0	0	0	0	0	1	0	1
VERSILUBE® F-50	23	0	0	0	0	0	0	0	0	0	1	0	1
VINEGAR	23	1	2	2	4	1	0	1	0	0	1	4	1
VINEGAR 5%	23	1	3	3	4	1	0	1	1	3	1	1	0
VINYL ACETATE	23	2	4	4	0	0	0	4	0	0	1	0	1
VINYL ACETYLENE	23	0	0	0	0	0	0	0	0	0	1	0	1
VINYL BENZENE	23	0	0	0	0	0	0	0	0	0	1	0	1
VINYL BENZOATE	23	0	0	0	0	0	0	0	0	0	1	0	1
VINYL CHLORIDE	23	4	4	4	4	4	2	1	1	1	1	4	1
VINYL FLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
VINYL METHYL ETHER	23	0	0	0	0	0	0	0	0	0	1	0	1
VINYL PYRIDINE	23	0	0	0	0	0	0	0	0	0	1	0	1
VINYLDENE CHLORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
VITRIOL (WHITE)	23	0	0	0	0	0	0	0	0	0	1	0	1
VV-B-680	23	1	2	0	3	4	0	1	0	0	1	3	1
VV-G-632	23	4	1	0	1	3	0	1	0	0	1	1	1
VV-G-671C	23	4	1	0	1	3	0	1	0	0	1	1	1
VV-H-910	23	1	2	3	3	4	0	1	0	0	1	3	1
VV-I-530A	23	4	1	0	2	3	0	1	0	0	1	2	1
VV-K-211D	23	4	1	0	3	4	0	1	0	0	1	3	1
VV-K-220A	23	4	1	0	2	4	0	1	0	0	1	2	1
VV-L-751B	23	4	2	0	3	4	0	1	0	0	1	3	1
VV-L-800	23	4	1	0	2	3	0	1	0	0	1	2	1
VV-L-820B	23	4	1	0	2	3	0	1	0	0	1	2	1
VV-L-825A TYPE I	23	4	1	0	1	3	0	1	0	0	1	1	1
VV-L-825A TYPE II	23	4	1	0	1	3	0	1	0	0	1	1	1
VV-L-825A TYPE III	23	4	2	0	3	4	0	1	0	0	1	3	1

- 0 = no data available
 1 = good, less than 5%
 2 = moderate, between 5% and 10%
 3 = not so good, between 10% and 20%
 4 = no good

	TEMPERATURA	EPDM	NBR	HNBR	POLIURETANI	SILICONE	AFLAS	FPM	POM	PA	PTFE	SINTEK HTPU	UHMW PE
VV-O-526	23	4	1	0	1	3	0	1	0	0	1	1	1
VV-P-216A	23	4	1	0	2	3	0	1	0	0	1	2	1
VV-P-236	23	4	2	0	3	4	0	1	0	0	1	3	1
WAGNER 21B BRAKE FLUID	23	1	3	3	4	3	0	4	0	0	1	4	1
WATER - DRINKING COLD	23	1	1	1	1	1	0	1	1	3	1	1	0
WATER - DRINKING HOT	80	1	3	1	4	1	0	3	1	3	1	1	0
WATER - DRINKING MINERAL	50	1	1	1	4	1	0	1	1	3	1	1	0
WATER - DRINKING WARM	40	1	2	1	2	0	0	1	1	3	1	1	0
WEMCO C	23	0	0	0	0	0	0	0	0	0	1	0	1
WHISKEY, WINES	23	1	1	1	2	1	0	1	0	0	1	2	1
WHITE LIQUOR	23	0	0	0	0	0	0	0	0	0	1	0	1
WHITE OIL	23	4	1	1	1	4	0	1	0	0	1	1	1
WHITE PINE OIL	23	4	2	0	0	4	0	1	0	0	1	0	1
WOLMAR SALTS	23	0	0	0	0	0	0	0	0	0	1	0	1
WOOD OIL	23	4	1	1	3	4	0	1	1	1	1	3	1
WORCESTERSHIRE SAUCE	23	0	0	0	0	0	0	0	0	0	1	0	1
XENON	23	1	1	1	1	1	0	1	1	1	1	0	1
XYLENE	23	4	4	4	4	4	0	4	1	1	1	4	0
XYLIDINE (DI-METHYL ANILINE)	23	2	3	3	4	4	0	4	0	0	1	4	1
YEAST, AQ. SOL.	30	1	1	1	4	1	0	1	1	1	1	0	1
YOGHURT	50	1	1	1	4	1	0	1	1	1	1	0	0
ZEOLITES	23	1	1	1	0	0	0	1	0	0	1	0	1
ZINC ACETATE	23	1	3	2	4	4	0	4	0	0	1	0	1
ZINC ACETATE (AQ)	23	1	2	2	4	4	0	4	0	0	1	4	1
ZINC AMMONIUM CHLORIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
ZINC CARBONATE	23	1	0	0	1	0	0	0	0	0	1	0	1
ZINC CHLORIDE	23	1	1	1	2	0	0	1	0	0	1	0	1
ZINC CHLORIDE (AQ)	23	1	1	1	1	1	1	1	0	0	1	1	1
ZINC CHROMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC CYANIDE	23	1	0	0	0	0	0	0	0	0	0	0	1
ZINC DIETHYLDITHIOCARBAMATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC DIHYDROGEN PHOSPHATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC FLUOROSILICATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC HYDROSULFITE	23	1	0	0	0	0	0	0	0	0	1	0	1
ZINC NAPHTHENATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC NITRATE	23	1	0	0	0	0	0	0	0	0	0	0	1
ZINC OXIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC PHENOLSULFONATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC PHOSPHATE	23	1	0	0	0	0	0	0	0	0	0	0	1
ZINC SALTS	23	1	1	1	1	0	0	1	0	0	1	0	1
ZINC SILICOFLUORIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC STEARATE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZINC SULFATE	23	2	1	1	2	0	0	1	0	0	1	0	1
ZINC SULFIDE	23	0	0	0	0	0	0	0	0	0	1	0	1
ZIRCONIUM NITRATE	23	0	0	0	0	0	0	0	0	0	1	0	1